

TITLE OF THE INVENTION

NOVEL (CO)POLYMERS AND A NOVEL POLYMERIZATION PROCESS BASED ON
ATOM (OR GROUP) TRANSFER RADICAL POLYMERIZATION

BACKGROUND OF THE INVENTIONField of the Invention

The present invention concerns novel (co)polymers and a novel radical polymerization process based on transition metal-mediated atom or group transfer polymerization ("atom transfer radical polymerization").

Discussion of the Background

Living polymerization renders unique possibilities of preparing a multitude of polymers which are well-defined in terms of molecular dimension, polydispersity, topology, composition, functionalization and microstructure. Many living systems based on anionic, cationic and several other types of initiators have been developed over the past 40 years (see O.W. Webster, *Science*, 251, 887 (1991)).

However, in comparison to other living systems, living radical polymerization represented a poorly answered challenge prior to the present invention. It was difficult to control the molecular weight and the polydispersity to achieve a highly uniform product of desired structure by prior radical polymerization processes.

On the other hand, radical polymerization offers the advantages of being applicable to polymerization of a wide variety of commercially important monomers, many of which cannot be polymerized by other polymerization processes.

5 Moreover, it is easier to make random copolymers by radical polymerization than by other (e.g., ionic) polymerization processes. Certain block copolymers cannot be made by other polymerization processes. Further, radical polymerization processes can be conducted in bulk, in solution, in suspension or in an emulsion, in contrast to other polymerization processes.

10 Thus, a need is strongly felt for a radical polymerization process which provides (co)polymers having a predetermined molecular weight, a narrow molecular weight distribution (low "polydispersity"), various topologies and controlled, uniform structures.

15 Three approaches to preparation of controlled polymers in a "living" radical process have been described (Greszta et al, *Macromolecules*, **27**, 638 (1994)). The first approach involves the situation where growing radicals react reversibly with scavenging radicals to form covalent species. The second approach involves the situation where growing radicals react reversibly with covalent species to produce persistent radicals. The third approach involves the situation where growing radicals participate in a degenerative transfer reaction which regenerates the same type of radicals.

BBB
CZ
"SECRET"

There are some patents and articles on living/controlled radical polymerization. Some of the best-controlled polymers obtained by "living" radical polymerization are prepared with preformed alkoxyamines or are those prepared *in situ* (U.S. Patent 4,581,429; Georges et al, *Macromolecules*, **26**, 2987 (1993)). A Co-containing complex has been used to prepare "living" polyacrylates (Wayland, B. B., Pszmik, G., Mukerjee, S. L., Fryd, M. J. *Am. Chem. Soc.*, **116**, 7943 (1994)). A "living" poly(vinyl acetate) can be prepared using an Al(*i*-Bu)₃: Bpy:TEMPO initiating system (Mardare et al, *Macromolecules*, **27**, 645 (1994)). An initiating system based on benzoyl peroxide and chromium acetate has been used to conduct the controlled radical polymerization of methyl methacrylate and vinyl acetate (Lee et al, *J. Chem. Soc. Trans. Faraday Soc. I*, **74**, 1726 (1978); Mardare et al, *Polym. Prep. (ACS)*, **36**(1) (1995)).

However, none of these "living" polymerization systems include an atom transfer process based on a redox reaction with a transition metal compound.

One paper describes a redox iniferter system based on Ni(0) and benzyl halides. However, a very broad and bimodal molecular weight distribution was obtained, and the initiator efficiency based on benzyl halides used was < 1% (T. Otsu, T. Tashinori, M. Yoshioka, *Chem. Express* 1990, **5**(10), 801).

Another paper describes the polymerization of methyl methacrylate, initiated by CCl₄ in the presence of RuCl₂(PPh₃)₃.


RECEIVED
24 FEB 1995
SAR
BB
C

However, the reaction does not occur without methylaluminum bis(2,6-di-tert-butylphenoxide), added as an activator (see M. Kato, M. Kamigaito, M. Sawamoto, T. Higashimura, *Macromolecules*, **28**, 1721 (1995)). This system is similar to the redox initiators developed early (Bamford, in *Comprehensive Polymer Science (First Supplement)*, Allen, G., Aggarwal, S. L., Russo, S., eds., Pergamon: Oxford, 1991, vol. 3, p. 123), in which the small amount of initiating radicals were generated by redox reaction between (1) $RCHX_2$ or RCX_3 (where $X = Br, Cl$) and (2) $Ni(0)$ and other transition metals. The reversible deactivation of initiating radicals by oxidized Ni is very slow in comparison with propagation, resulting in very low initiator efficiency and a very broad and bimodal molecular weight distribution.

Atom transfer radical addition, ATRA, is a well-known method for carbon-carbon bond formation in organic synthesis. (For reviews of atom transfer methods in organic synthesis, see (a) Curran, D. P. *Synthesis*, **1988**, 489; (b) Curran, D. P. in *Free Radicals in Synthesis and Biology*, Minisci, F., ed., Kluwer: Dordrecht, 1989, p. 37; and (c) Curran, D. P. in *Comprehensive Organic Synthesis*, Trost, B. M., Fleming, I., eds., Pergamon: Oxford, 1991, Vol. 4, p. 715.) In a very broad class of ATRA, two types of atom transfer methods have been largely developed. One of them is known as atom abstraction or homolytic substitution (see (a) Curran et al, *J. Org. Chem.*, **1989**, 54, 3140; and (b) Curran et al, *J. Am.*

Chem. Soc., 1994, 116, 4279), in which a univalent atom (typically a halogen) or a group (such as SPh or SePh) is transferred from a neutral molecule to a radical to form a new σ -bond and a new radical in accordance with Scheme 1 below:

5 Scheme 1:



X = I, SePh, SPh,...

10 In this respect, iodine atom and the SePh group were found to work very well, due to the presence of very weak C-I and C-SePh bonds towards the reactive radicals (Curran et al, *J. Org. Chem.* and *J. Am. Chem. Soc.*, *supra*). In earlier work, the present inventors have discovered that alkyl iodides may induce the degenerative transfer process in radical polymerization, leading to a controlled radical polymerization of several alkenes. This is consistent with the fact that 15 alkyl iodides are outstanding iodine atom donors that can undergo a fast and reversible transfer in an initiation step and degenerative transfer in a propagation step (see Gaynor et al, *Polym. Prep. (Am. Chem. Soc., Polym. Chem. Div.)*, 1995, 36(1), 467; Wang et al, *Polym. Prep. (Am. Chem. Soc., Polym. Chem. Div.)*, 1995, 36(1), 465).

20 Another atom transfer method is promoted by a transition metal species (see (a) Bellus, D. *Pure & Appl. Chem.* 1985, 57, 1827; (b) Nagashima, H.; Ozaki, N.; Ishii, M.; Seki, K.;

Washiyama, M.; Itoh, K. *J. Org. Chem.* **1993**, 58, 464; (c) Udding, J. H.; Tuijp, K. J. M.; van Zanden, M. N. A.; Hiemstra, H.; Speckamp, W. N. *J. Org. Chem.* **1994**, 59, 1993; (c) Seijas et al, *Tetrahedron*, **1992**, 48(9), 1637; (d) 5 Nagashima, H.; Wakamatsu, H.; Ozaki, N.; Ishii, T.; Watanabe, M.; Tajima, T.; Itoh, K. *J. Org. Chem.* **1992**, 57, 1682; (e) Hayes, T. K.; Villani, R.; Weinreb, S. M. *J. Am. Chem. Soc.* **1988**, 110, 5533; (f) Hirao et al, *Syn. Lett.*, **1990**, 217; and (g) Hirao et al, *J. Synth. Org. Chem. (Japan)*, **1994**, 52(3), 197; (h) Iqbal, J; Bhatia, B.; Nayyar, N. K. *Chem. Rev.*, **94**, 519 (1994)). In these reactions, a catalytic amount of transition metal compound acts as a carrier of the halogen atom in a redox process, in accordance with Figure 1.

Initially, the transition metal species, M_t^n , abstracts 15 halogen atom X from the organic halide, R-X, to form the oxidized species, $M_t^{n+1}X$, and the carbon-centered radical R^\cdot . In the subsequent step, the radical, R^\cdot , reacts with alkene, M, with the formation of the intermediate radical species, R-M $^\cdot$. The reaction between $M_t^{n+1}X$ and R-M $^\cdot$ results in the target 20 product, R-M-X, and regenerates the reduced transition metal species, M_t^n , which further reacts with R-X and promotes a new redox process.

The high efficiency of transition metal-catalyzed atom transfer reactions in producing the target product, R-M-X, in 25 good to excellent yields (often > 90%) may suggest that the presence of an M_t^n/M_t^{n+1} cycle-based redox process can

SYN
DB
CUB
366000 2874000

effectively compete with the bimolecular termination reactions between radicals (see Curran, *Synthesis*, in *Free Radicals in Synthesis and Biology*, and in *Comprehensive Organic Synthesis*, *supra*).

5 It is difficult to control the molecular weight and the polydispersity (molecular weight distribution) of polymers produced by radical polymerization. Thus, it is often difficult to achieve a highly uniform and well-defined product. It is also often difficult to control radical polymerization processes with the degree of certainty necessary in specialized applications, such as in the preparation of end functional polymers, block copolymers, star (co)polymers, etc. Further, although several initiating systems have been reported for "living"/controlled
15 polymerization, no general pathway or process for "living"/controlled polymerization has been discovered.

Thus, a need is strongly felt for a radical polymerization process which provides (co)polymers having a predictable molecular weight and a narrow molecular weight
20 distribution (low "polydispersity"). A further need is strongly felt for a radical polymerization process which is sufficiently flexible to provide a wide variety of products, but which can be controlled to the degree necessary to provide highly uniform products with a controlled structure (i.e.,
25 controllable topology, composition, stereoregularity, etc.), many of which are suitable for highly specialized uses (such

5
10
15
20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100
105
110
115
120
125
130
135
140
145
150
155
160
165
170
175
180
185
190
195
200
205
210
215
220
225
230
235
240
245
250
255
260
265
270
275
280
285
290
295
300
305
310
315
320
325
330
335
340
345
350
355
360
365
370
375
380
385
390
395
400
405
410
415
420
425
430
435
440
445
450
455
460
465
470
475
480
485
490
495
500
505
510
515
520
525
530
535
540
545
550
555
560
565
570
575
580
585
590
595
600
605
610
615
620
625
630
635
640
645
650
655
660
665
670
675
680
685
690
695
700
705
710
715
720
725
730
735
740
745
750
755
760
765
770
775
780
785
790
795
800
805
810
815
820
825
830
835
840
845
850
855
860
865
870
875
880
885
890
895
900
905
910
915
920
925
930
935
940
945
950
955
960
965
970
975
980
985
990
995
1000

as thermoplastic elastomers, end-functional polymers for chain-extended polyurethanes, polyesters and polyamides, dispersants for polymer blends, etc.).

SUMMARY OF THE INVENTION

5 Accordingly, one object of the present invention is to provide a novel method for radical polymerization of alkenes based on atom transfer radical polymerization (ATRP), which provides a high degree of control over the polymerization process.

10 A further object of the present invention is to provide a novel method for radical polymerization of alkenes based on atom transfer radical polymerization (ATRP), which leads to more uniform and more highly controllable products (which are now obtainable only by living ionic polymerization methods).

15 A further object of the present invention is to provide a broad variety of novel (co)polymers having more uniform properties than those obtained by conventional radical polymerization.

20 These and other objects of the present invention, which will be readily understood in the context of the following detailed description of the preferred embodiments, have been provided in part by a novel process of atom (or group) radical transfer polymerization, which comprises the steps of:

25 polymerizing one or more radically polymerizable monomers in the presence of an initiator having a radically

RECEIVED "ZATTEBO"

SV
BB

transferable atom or group, a transition metal compound and a ligand to form a (co)polymer, the transition metal compound having a formula $M_t^{n+}X'_n$, and the ligand being any N-, O-, P- or S- containing compound which can coordinate in a σ -bond or any carbon-containing compound which can coordinate in a π -bond to the transition metal, such that direct (i.e., covalent) bonds between the transition metal and growing polymer radicals are not formed, and

isolating the formed (co)polymer;

and, in part, by novel (co)polymers prepared by atom (or group) radical transfer polymerization.

BRIEF DESCRIPTION OF THE FIGURES

Figure 1 shows an atom transfer method in which a catalytic amount of transition metal catalyst acts as a carrier of the halogen atom in a redox process;

Figure 2 shows a scheme for "living"/controlled radical polymerization based on a succession of atom transfer radical additions;

Figure 3 is a graph of the kinetics of methyl acrylate ("MA") bulk polymerization at 130°C, initiated with 1-phenylethyl chloride in the presence of Cu(I)Cl (1 equiv.) and bipyridine (Bpy; 3 equiv.);

Figure 4 is a graph showing that the experimental molecular weight, $M_{n, SEC}$, increases with monomer conversion;

Figure 5 is a graph showing that the experimental molecular weight, $M_{n,SEC}$, matches the theoretical molecular weight, $M_{n,th}$, and plotting the polydispersity, M_w/M_n , as a function of monomer conversion;

5 Figure 6 shows the correlation of the experimental molecular weights, $M_{n,SEC}$, with the theoretical molecular weights, $M_{n,th}$, for a series of bulk ATRP's of MA carried out at 130°C using various monomer/initiator molar ratios and a constant ligand/catalyst/initiator molar ratio of 3/1/1;

10 Figures 7A and 7B show the 1H NMR spectra of PST prepared at 130°C using 2-chloropropionitrile as an initiator, in the presence of 1 molar equiv. of CuCl and 3 molar equiv. of Bpy;

15 Figures 8A and 8B compare the ^{13}C NMR spectra of the C=O group and the quaternary carbon atom of PMMA prepared at 100°C using methyl 2-bromoisobutyrate ("2-MiBBR"), CuBr and Bpy in a 1/1/3 molar ratio (Fig. 8A), and of PMMA prepared using a classic radical initiator, AIBN (Fig. 8B);

20 Figure 9 shows the kinetic plots of the ATRP of three typical monomers (styrene, "St", methyl acrylate, "MA", and methyl methacrylate, "MMA") using the 1/1/3 1-PECl/CuCl/Bpy initiator system, under the same experimental conditions (in bulk, at 130°C);

25 Figures 10 and 11 are graphs comparing the experimental molecular weight, $M_{n,SEC}$, with the theoretical molecular weight, $M_{n,th}$, and plotting the polydispersity, M_w/M_n , as a function of

RECEIVED "ATHEOEO"

SV
BB

monomer conversion when $X = X' = \text{Cl}$ ("Cl ATRP"; Fig. 10) and when $X = X' = \text{Br}$ ("Br ATRP"; Fig. 11);

Figures 12A-C show plots of $\ln(k_p^{\text{app}})$ vs. $\ln([1-\text{PECl}]_0)$, $\ln(k_p^{\text{app}})$ vs. $\ln([\text{CuCl}]_0)$, and $\ln(k_p^{\text{app}})$ vs $\ln([\text{Bpy}]_0)$ for St ATRP in bulk at 130°C;

Figures 13A-C are graphs showing the effects of $[\text{CuCl}]_0$ on the initiator efficiency and the molecular weight distribution for St ATRP in bulk at 130°C;

Figures 14A-B are graphs demonstrating similar results for MA ATRP;

Figure 15 is a scheme showing an overall two-electron change in which Cu(I)Cl cleaves a carbon-halogen bond to generate a Cu(III) species, followed by insertion of the alkene into the carbon-copper(III) σ -bond and halogen ligand transfer (reductive elimination);

Figure 16 shows a putative insertion process;

Figure 17 shows a putative process involving metal coordinated radicals; and

Figures 18A and 18B show two different mechanisms for the generation of free radicals by reacting an organic halide with a transition metal compound, involving either halogen atom transfer (Figure 18A) or outer-sphere electron transfer (Figure 18B).

RECEIVED

5
10
15
20

DESCRIPTION OF THE PREFERRED EMBODIMENTS

5 The present Inventors conceptualized that if (1) the organic halide $R-M_1-X$ resulting from an ATRA reaction is sufficiently reactive towards the transition metal M_2^n and (2) the alkene monomer is in excess, a number or sequence of atom transfer radical additions (i.e., a possible "living"/ controlled radical polymerization) may occur, as is shown in Fig. 2.

By analogy to ATRA, the present ^l~~I~~nventors have termed this new class of radical polymerization "atom (or group) transfer radical polymerization" (or "ATRP"), which describes the involvement of (1) the atom or group transfer pathway and (2) a radical intermediate.

Living/controlled polymerization (i.e., when chain breaking reactions such as transfer and termination are substantially absent) enables control of various parameters of macromolecular structure such as molecular weight, molecular weight distribution and terminal functionalities. It also allows the preparation of various copolymers, including block and star copolymers. Living/controlled radical polymerization requires a low stationary concentration of radicals, in equilibrium with various dormant species.

The present invention describes use of novel initiating systems leading to living/controlled radical polymerization. The initiation system is based on the reversible formation of growing radicals in a redox reaction between various

RECEIVED "PATHEO"

10

15

20

25

R2
8/1/99

5
BB

transition metal compounds and an initiator, exemplified by (but not limited to) alkyl halides, aralkyl halides or haloalkyl esters. Using 1-phenylethyl chloride (1-PECl) as a model initiator, CuCl as a model catalyst and bipyridine (Bpy) as a model ligand, a "living" radical bulk polymerization of styrene at 130°C affords the predicted molecular weight up to $M_n \approx 10^5$ with a narrow molecular weight distribution (e.g., $M_w/M_n < 1.5$).

A key factor in the present invention is to achieve rapid exchange between growing radicals present at low stationary concentrations (in the range of from 10^{-9} mol/L to 10^{-6} mol/L, preferably 10^{-8} mol/L to 10^{-6} mol/L) and dormant chains present at higher concentrations (typically in the range 10^{-4} mol/L to 1 mol/L, preferably 10^{-2} mol/L to 10^{-1} mol/L). It may be desirable to "match" the initiator/catalyst/ligand system and monomer(s) such that these concentration ranges are achieved.


Although these concentration ranges are not essential to conducting polymerization, certain disadvantageous effects may result if the concentration ranges are exceeded. For example, if the concentration of growing radicals exceeds 10^{-6} mol/L, there may be too many active species in the reaction, which may lead to an undesirable increase in the rate of side reactions (e.g., radical-radical quenching, radical abstraction from species other than the catalyst system, etc.). If the concentration of growing radicals is less than 10^{-9} mol/L, the rate may be undesirably slow.

10

15

20

25



5 wherein R^1 and R^2 are independently selected from the group consisting of H, halogen, CN, CF_3 , straight or branched alkyl of from 1 to 20 carbon atoms (preferably from 1 to 6 carbon atoms, more preferably from 1 to 4 carbon atoms), α, β -unsaturated straight or branched alkenyl or alkynyl of 2 to 10 carbon atoms (preferably from 2 to 6 carbon atoms, more preferably from 2 to 4 carbon atoms), α, β -unsaturated straight or branched alkenyl of 2 to 6 carbon atoms (preferably vinyl) substituted (preferably at the α -position) with a halogen (preferably chlorine), C_3 - C_8 cycloalkyl, heterocyclyl, $C(=Y)R^5$, $C(=Y)NR^6R^7$ and $YC(=Y)R^8$, where Y may be NR^8 or O (preferably O), R^5 is alkyl of from 1 to 20 carbon atoms, alkoxy of from 1 to 20 carbon atoms, aryloxy or heterocyclyloxy, R^6 and R^7 are independently H or alkyl of from 1 to 20 carbon atoms, or R^6 and R^7 may be joined together to form an alkylene group of from 2 to 5 carbon atoms, thus forming a 3- to 6-membered ring, and R^8 is H, straight or branched C_1 - C_{20} alkyl or aryl; and

R^3 and R^4 are independently selected from the group consisting of H, halogen (preferably fluorine or chlorine), C_1 - C_6 (preferably C_1) alkyl and $COOR^9$ (where R^9 is H, an alkali metal, or a C_1 - C_6 alkyl group); or

R^1 and R^2 may be joined to form a group of the formula $(CH_2)_{n'}$ (which may be substituted with from 1 to $2n'$ halogen

SECRETED BY THE GOVERNMENT

atoms or C₁-C₄ alkyl groups) or C(=O)-Y-C(=O), where n' is from 2 to 6 (preferably 3 or 4) and Y is as defined above; and at least two of R¹, R², R³ and R⁴ are H or halogen.

In the context of the present application, the terms "alkyl", "alkenyl" and "alkynyl" refer to straight-chain or branched groups (except for C₁ and C₂ groups).

Furthermore, in the present application, "aryl" refers to phenyl, naphthyl, phenanthryl, phenalenyl, anthracenyl, triphenylenyl, fluoranthenyl, pyrenyl, pentacenyl, chrysenyl, naphthacenyl, hexaphenyl, picenyl and perylenyl (preferably phenyl and naphthyl), in which each hydrogen atom may be replaced with alkyl of from 1 to 20 carbon atoms (preferably from 1 to 6 carbon atoms and more preferably methyl), alkyl of from 1 to 20 carbon atoms (preferably from 1 to 6 carbon atoms and more preferably methyl) in which each of the hydrogen atoms is independently replaced by a halide (preferably a fluoride or a chloride), alkenyl of from 2 to 20 carbon atoms, alkynyl of from 1 to 20 carbon atoms, alkoxy of from 1 to 6 carbon atoms, alkylthio of from 1 to 6 carbon atoms, C₃-C₈ cycloalkyl, phenyl, halogen, NH₂, C₁-C₆-alkylamino, C₁-C₆-dialkylamino, and phenyl which may be substituted with from 1 to 5 halogen atoms and/or C₁-C₄ alkyl groups. (This definition of "aryl" also applies to the aryl groups in "aryloxy" and "aralkyl.") Thus, phenyl may be substituted from 1 to 5 times and naphthyl may be substituted from 1 to 7 times (preferably, any aryl group, if substituted, is substituted from 1 to 3

5
BB
10
15
20
25
"SECRET"

times) with one of the above substituents. More preferably, "aryl" refers to phenyl, naphthyl, phenyl substituted from 1 to 5 times with fluorine or chlorine, and phenyl substituted from 1 to 3 times with a substituent selected from the group consisting of alkyl of from 1 to 6 carbon atoms, alkoxy of from 1 to 4 carbon atoms and phenyl. Most preferably, "aryl" refers to phenyl, tolyl and methoxyphenyl.

In the context of the present invention, "heterocyclyl" refers to pyridyl, furyl, pyrrolyl, thienyl, imidazolyl, pyrazolyl, pyrazinyl, pyrimidinyl, pyridazinyl, pyranyl, indolyl, isoindolyl, indazolyl, benzofuryl, isobenzofuryl, benzothienyl, isobenzothienyl, chromenyl, xanthenyl, purinyl, pteridinyl, quinolyl, isoquinolyl, phthalazinyl, quinazolinyl, quinoxalinyl, naphthyridinyl, phenoxathiinyl, carbazolyl, cinnolinyl, phenanthridinyl, acridinyl, 1,10-phenanthrolinyl, phenazinyl, phenoxazinyl, phenothiazinyl, oxazolyl, thiazolyl, isoxazolyl, isothiazolyl, and hydrogenated forms thereof known to those in the art. Preferred heterocyclyl groups include pyridyl, furyl, pyrrolyl, thienyl, imidazolyl, pyrazolyl, pyrazinyl, pyrimidinyl, pyridazinyl, pyranyl and indolyl, the most preferred heterocyclyl group being pyridyl. Accordingly, suitable vinyl heterocycles to be used as a monomer in the present invention include 2-vinyl pyridine, 6-vinyl pyridine, 2-vinyl pyrrole, 5-vinyl pyrrole, 2-vinyl oxazole, 5-vinyl oxazole, 2-vinyl thiazole, 5-vinyl thiazole, 2-vinyl imidazole, 5-vinyl imidazole, 3-vinyl pyrazole, 5-vinyl

RECEIVED "ARTHEO" 60

5
BB
cm

15

20


25

pyrazole, 3-vinyl pyridazine, 6-vinyl pyridazine, 3-vinyl
isoxazole, 3-vinyl isothiazoles, 2-vinyl pyrimidine, 4-vinyl
pyrimidine, 6-vinyl pyrimidine, and any vinyl pyrazine, the
most preferred being 2-vinyl pyridine. The vinyl heterocycles
mentioned above may bear one or more (preferably 1 or 2) C₁-C₆
alkyl or alkoxy groups, cyano groups, ester groups or halogen
atoms, either on the vinyl group or the heterocyclyl group,
but preferably on the heterocyclyl group. Further, those
vinyl heterocycles which, when unsubstituted, contain an N-H
group may be protected at that position with a conventional
blocking or protecting group, such as a C₁-C₆ alkyl group, a
tris-C₁-C₆ alkylsilyl group, an acyl group of the formula R¹⁰CO
(where R¹⁰ is alkyl of from 1 to 20 carbon atoms, in which each
of the hydrogen atoms may be independently replaced by halide
[preferably fluoride or chloride]), alkenyl of from 2 to 20
carbon atoms (preferably vinyl), alkynyl of from 2 to 10
carbon atoms (preferably acetylenyl), phenyl which may be
substituted with from 1 to 5 halogen atoms or alkyl groups of
from 1 to 4 carbon atoms, or aralkyl (aryl-substituted alkyl,
in which the aryl group is phenyl or substituted phenyl and
the alkyl group is from 1 to 6 carbon atoms), etc. (This
definition of "heterocyclyl" also applies to the heterocyclyl
groups in "heterocyclloxy" and "heterocyclic ring.")

More specifically, preferred monomers include
(meth)acrylate esters of C₁-C₂₀ alcohols, acrylonitrile,
cyanoacrylate esters of C₁-C₂₀ alcohols, didehydromalonate

diesters of C₁-C₆ alcohols, vinyl pyridines, vinyl N-C₁-C₆-alkylpyrroles, vinyl oxazoles, vinyl thiazoles, vinyl pyrimidines and vinyl imidazoles, vinyl ketones in which the α-carbon atom of the alkyl group does not bear a hydrogen atom (e.g., vinyl C₁-C₆-alkyl ketones in which both α-hydrogens are replaced with C₁-C₄ alkyl, halogen, etc., or a vinyl phenyl ketone in which the phenyl may be substituted with from 1 to 5 C₁-C₅-alkyl groups and/or halogen atoms), and styrenes which may bear a C₁-C₆-alkyl group on the vinyl moiety (preferably at the α-carbon atom) and from 1 to 5 (preferably from 1 to 3) substituents on the phenyl ring selected from the group consisting of C₁-C₅-alkyl, C₁-C₆-alkenyl (preferably vinyl), C₁-C₆-alkynyl (preferably acetylenyl), C₁-C₆-alkoxy, halogen, nitro, carboxy, C₁-C₆-alkoxycarbonyl, hydroxy protected with a C₁-C₆ acyl, cyano and phenyl. The most preferred monomers are methyl acrylate (MA), methyl methacrylate (MMA), butyl acrylate (BA), 2-ethylhexyl acrylate (EHA), acrylonitrile (AN) and styrene.

Suitable initiators include those of the formula:



where:

X is selected from the group consisting of Cl, Br, I, OR¹⁰ (as defined above), SR¹⁴, SeR¹⁴, OC(=O)R¹⁴, OP(=O)R¹⁴, OP(=O)(OR¹⁴)₂, OP(=O)OR¹⁴, O-N(R¹⁴)₂ and S-C(=S)N(R¹⁴)₂, where R¹⁴

is aryl or a straight or branched C_1-C_{20} (preferably C_1-C_{10}) alkyl group, or where an $N(R^{14})_2$ group is present, the two R^{14} groups may be joined to form a 5-, 6- or 7-membered heterocyclic ring (in accordance with the definition of "heterocyclyl" above); and

5 R^{11} , R^{12} and R^{13} are each independently selected from the group consisting of H, halogen, C_1-C_{20} alkyl (preferably C_1-C_{10} alkyl and more preferably C_1-C_6 alkyl), C_3-C_8 cycloalkyl, $C(=Y)R^5$, $C(=Y)NR^6R^7$ (where R^5-R^7 are as defined above), $COCl$, OH
10 (preferably only one of R^{11} , R^{12} and R^{13} is OH), CN, C_2-C_{20} alkenyl or alkynyl (preferably C_2-C_6 alkenyl or alkynyl, and more preferably vinyl), oxiranyl, glycidyl, aryl, heterocyclyl, aralkyl, aralkenyl (aryl-substituted alkenyl, where aryl is as defined above, and alkenyl is vinyl which may
15 be substituted with one or two C_1-C_6 alkyl groups and/or halogen atoms [preferably chlorine]), C_1-C_6 alkyl in which from 1 to all of the hydrogen atoms (preferably 1) are replaced with halogen (preferably fluorine or chlorine where 1 or more hydrogen atoms are replaced, and preferably fluorine, chlorine
20 or bromine where 1 hydrogen atom is replaced) and C_1-C_6 alkyl substituted with from 1 to 3 substituents (preferably 1) selected from the group consisting of C_1-C_4 alkoxy, aryl, heterocyclyl, $C(=Y)R^5$ (where R^5 is as defined above), $C(=Y)NR^6R^7$ (where R^6 and R^7 are as defined above), oxiranyl and glycidyl;
25 such that no more than two of R^{11} , R^{12} and R^{13} are H (preferably no more than one of R^{11} , R^{12} and R^{13} is H).

RECEIVED "PATENTED"

In the present initiator, X is preferably Cl or Br. Cl-containing initiators generally provide (1) a slower reaction rate and (2) higher product polydispersity than the corresponding Br-containing initiators. Thus, a Br-containing initiator is most preferred.

When an alkyl, cycloalkyl, or alkyl-substituted aryl group is selected for one of R^{11} , R^{12} and R^{13} , the alkyl group may be further substituted with an X group as defined above. Thus, it is possible for the initiator to serve as a starting molecule for branch or star (co)polymers. One example of such an initiator is a 2,2-bis(halomethyl)-1,3-dihalopropane (e.g., 2,2-bis(chloromethyl)-1,3-dichloropropane, 2,2-bis(bromomethyl)-1,3-dibromopropane), and a preferred example is where one of R^{11} , R^{12} and R^{13} is phenyl substituted with from one to five C_1 - C_6 alkyl substituents, each of which may independently be further substituted with a X group (e.g., α, α' -dibromoxylene, hexakis(α -chloro- or α -bromomethyl)-benzene).

Preferred initiators include 1-phenylethyl chloride and 1-phenylethyl bromide (e.g., where $R^{11} = \text{Ph}$, $R^{12} = \text{CH}_3$, $R^{13} = \text{H}$ and $X = \text{Cl}$ or Br), chloroform, carbon tetrachloride, 2-chloropropionitrile, C_1 - C_6 -alkyl esters of a 2-halo- C_1 - C_6 -carboxylic acid (such as 2-chloropropionic acid, 2-bromopropionic acid, 2-chloroisobutyric acid, 2-bromoisobutyric acid, etc.) and compounds of the formula $\text{C}_6\text{H}_x(\text{CH}_2\text{Y}')_y$, where Y' is Cl or Br, $x + y = 6$ and $y \geq 1$. More

preferred initiators include 1-phenylethyl chloride, 1-phenylethyl bromide, methyl 2-chloropropionate, ethyl 2-chloropropionate, methyl 2-bromopropionate, ethyl 2-bromoisobutyrate, α,α' -dichloroxylene, α,α' -dibromoxylene and hexakis(α -bromomethyl)benzene.

Any transition metal compound which can participate in a redox cycle with the initiator and dormant polymer chain, but which does not form a direct carbon-metal bond with the polymer chain, is suitable for use in the present invention.

Preferred transition metal compounds are those of the formula $M_t^{n+}X'_n$, where:



M_t^{n+} may be selected from the group consisting of Cu^{1+} , Cu^{2+} , Fe^{2+} , Fe^{3+} , Ru^{2+} , Ru^{3+} , Cr^{2+} , Cr^{3+} , Mo^0 , Mo^+ , Mo^{2+} , Mo^{3+} , W^{2+} , W^{3+} , Rh^{3+} , Rh^{4+} , Co^+ , Co^{2+} , Re^{2+} , Re^{3+} , Ni^0 , Ni^+ , Mn^{3+} , Mn^{4+} , V^{2+} , V^{3+} , Zn^+ , Zn^{2+} , Au^+ , Au^{2+} , Ag^+ and Ag^{2+} ;

X' is selected from the group consisting of halogen, C_1 - C_6 -alkoxy, $(SO_4)_{1/2}$, $(PO_4)_{1/3}$, $(HPO_4)_{1/2}$, (H_2PO_4) , triflate, hexafluorophosphate, methanesulfonate, arylsulfonate (preferably benzenesulfonate or toluenesulfonate), SeR^{14} , CN and $R^{15}CO_2$, where R^{14} is as defined above and R^{15} is H or a straight or branched C_1 - C_6 alkyl group (preferably methyl) which may be substituted from 1 to 5 times with a halogen (preferably 1 to 3 times with fluorine or chlorine); and

n is the formal charge on the metal (e.g., $0 \leq n \leq 7$).

Suitable ligands for use in the present invention include ligands having one or more nitrogen, oxygen, phosphorus and/or

sulfur atoms which can coordinate to the transition metal through a σ -bond, ligands containing two or more carbon atoms which can coordinate to the transition metal through a π -bond, and ligands which can coordinate to the transition metal through a μ -bond or a η -bond. However, preferred N-, O-, P- and S- containing ligands may have one of the following formulas:



where:

R^{16} and R^{17} are independently selected from the group consisting of H, C_1-C_{20} alkyl, aryl, heterocyclyl, and C_1-C_6 alkyl substituted with C_1-C_6 alkoxy, C_1-C_4 dialkylamino, $C(=Y)R^5$, $C(=Y)R^6R^7$ and $YC(=Y)R^8$, where Y, R^5 , R^6 , R^7 and R^8 are as defined above; or

R^{16} and R^{17} can be joined to form a saturated, unsaturated or heterocyclic ring as described above for the "heterocyclyl" group;

Z is O, S, NR^{19} or PR^{19} , where R^{19} is selected from the same group as R^{16} and R^{17} ,

each R^{18} is independently a divalent group selected from the group consisting of C_2-C_4 alkylene (alkanediyl) and C_2-C_4 alkenylene where the covalent bonds to each Z are at vicinal positions (e.g., in a 1,2-arrangement) or at β -positions (e.g., in a 1,3-arrangement), and from C_3-C_8 cycloalkanediyl,

RECEIVED "RESEARCH"

5
BB
ent

C₃-C₈ cycloalkenediyl, arenediyl and heterocyclylene where the covalent bonds to each Z are at vicinal positions; and

m is from 1 to 6.

5 In addition to the above ligands, each of R¹⁶-Z and R¹⁷-Z can form a ring with the R¹⁸ group to which the Z is bound to form a linked or fused heterocyclic ring system (such as is described above for "heterocyclyl"). Alternatively, when R¹⁶ and/or R¹⁷ are heterocyclyl, Z can be a covalent bond (which may be single or double), CH₂ or a 4- to 7-membered ring fused to R¹⁶ and/or R¹⁷, in addition to the definitions given above for Z. Exemplary ring systems for the present ligand include bipyridine, bipyrrrole, 1,10-phenanthroline, a cryptand, a crown ether, etc.

Where Z is PR¹⁹, R¹⁹ can also be C₁-C₂₀-alkoxy.

15 Also included as suitable ligands in the present invention are CO (carbon monoxide), porphyrins and porphycenes, the latter two of which may be substituted with from 1 to 6 (preferably from 1 to 4) halogen atoms, C₁-C₆ alkyl groups, C₁-C₆-alkoxy groups, C₁-C₆ alkoxycarbonyl, aryl groups, 20 heterocyclyl groups, and C₁-C₆ alkyl groups further substituted with from 1 to 3 halogens.

Further ligands suitable for use in the present invention include compounds of the formula R²⁰R²¹C(C(=Y)R⁵)₂, where Y and R⁵ are as defined above, and each of R²⁰ and R²¹ is 25 independently selected from the group consisting of H, halogen, C₁-C₂₀ alkyl, aryl and heterocyclyl, and R²⁰ and R²¹ may

be joined to form a C_3-C_8 cycloalkyl ring or a hydrogenated (i.e., reduced, non-aromatic or partially or fully saturated) aromatic or heterocyclic ring (consistent with the definitions of "aryl" and "heterocyclyl" above), any of which (except for H and halogen) may be further substituted with 1 to 5 and preferably 1 to 3 C_1-C_6 alkyl groups, C_1-C_6 alkoxy groups, halogen atoms and/or aryl groups. Preferably, one of R^{20} and R^{21} is H or a negative charge.

Additional suitable ligands include, for example, ethylenediamine and propylenediamine, both of which may be substituted from one to four times on the amino nitrogen atom with a C_1-C_4 alkyl group or a carboxymethyl group; aminoethanol and aminopropanol, both of which may be substituted from one to three times on the oxygen and/or nitrogen atom with a C_1-C_4 alkyl group; ethylene glycol and propylene glycol, both of which may be substituted one or two times on the oxygen atoms with a C_1-C_4 alkyl group; diglyme, triglyme, tetraglyme, etc.

Suitable carbon-based ligands include arenes (as described above for the "aryl" group) and the cyclopentadienyl ligand. Preferred carbon-based ligands include benzene (which may be substituted with from one to six C_1-C_4 alkyl groups [e.g., methyl]) and cyclopentadienyl (which may be substituted with from one to five methyl groups, or which may be linked through an ethylene or propylene chain to a second cyclopentadienyl ligand). Where the cyclopentadienyl ligand

is used, it may not be necessary to include a counteranion (X') in the transition metal compound.

Preferred ligands include unsubstituted and substituted pyridines and bipyridines (where the substituted pyridines and bipyridines are as described above for "heterocyclyl"), acetonitrile, $(R^{10}O)_3P$, PR^{10} , 1,10-phenanthroline, porphyrin, cryptands such as K_{22} and crown ethers such as 18-crown-6. The most preferred ligands are bipyridine and $(R^{10}O)_3P$.

In the present polymerization, the amounts and relative proportions of initiator, transition metal compound and ligand are those effective to conduct ATRP. Initiator efficiencies with the present initiator/transition metal compound/ligand system are generally very good (at least 50%, preferably $\geq 80\%$, more preferably $\geq 90\%$). Accordingly, the amount of initiator can be selected such that the initiator concentration is from 10^{-4} M to 1 M, preferably 10^{-3} - 10^{-1} M. Alternatively, the initiator can be present in a molar ratio of from 10^{-4} :1 to 10^{-1} :1, preferably from 10^{-3} :1 to 5×10^{-2} :1, relative to monomer. An initiator concentration of 0.1-1 M is particularly useful for preparing end-functional polymers.

The molar proportion of transition metal compound relative to initiator is generally that which is effective to polymerize the selected monomer(s), but may be from 0.0001:1 to 10:1, preferably from 0.1:1 to 5:1, more preferably from 0.3:1 to 2:1, and most preferably from 0.9:1 to 1.1:1. Conducting the polymerization in a homogeneous system may

permit reducing the concentration of transition metal and ligand such that the molar proportion of transition metal compound to initiator is as low as 0.001:1.

5
10
15
20
Similarly, the molar proportion of ligand relative to transition metal compound is generally that which is effective to polymerize the selected monomer(s), but can depend upon the number of coordination sites on the transition metal compound which the selected ligand will occupy. (One of ordinary skill understands the number of coordination sites on a given transition metal compound which a selected ligand will occupy.) The amount of ligand may be selected such that the ratio of (a) coordination sites on the transition metal compound to (b) coordination sites which the ligand will occupy is from 0.1:1 to 100:1, preferably from 0.2:1 to 10:1, more preferably from 0.5:1 to 3:1, and most preferably from 0.8:1 to 2:1. However, as is also known in the art, it is possible for a solvent or for a monomer to act as a ligand. For the purposes of this application, a monomer is treated as being (a) distinct from and (b) not included within the scope of the ligand.

25
The present polymerization may be conducted in the absence of solvent ("bulk" polymerization). However, when a solvent is used, suitable solvents include ethers, cyclic ethers, C₅-C₁₀ alkanes, C₅-C₈ cycloalkanes which may be substituted with from 1 to 3 C₁-C₄ alkyl groups, aromatic hydrocarbon solvents, halogenated hydrocarbon solvents,

RECEIVED "LATE" 1960

5
10
15
20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100

Suitable ethers include compounds of the formula $R^{22}OR^{23}$, in which each of R^{22} and R^{23} is independently an alkyl group of from 1 to 6 carbon atoms which may be further substituted with a C_1 - C_4 -alkoxy group. Preferably, when one of R^{22} and R^{23} is methyl, the other of R^{22} and R^{23} is alkyl of from 4 to 6 carbon atoms or C_1 - C_4 -alkoxyethyl. Examples include diethyl ether, ethyl propyl ether, dipropyl ether, methyl t-butyl ether, di-t-butyl ether, glyme (dimethoxyethane), diglyme (diethylene glycol dimethyl ether), etc.

Suitable cyclic ethers include THF and dioxane. Suitable aromatic hydrocarbon solvents include benzene, toluene, o-xylene, m-xylene, p-xylene and any isomer or mixture of isomers of cumene. Suitable halogenated hydrocarbon solvents include CH_2Cl_2 , 1,2-dichloroethane and benzene substituted from 1 to 6 times with fluorine and/or chlorine, although one should ensure that the selected halogenated hydrocarbon solvent(s) does not act as an initiator under the reaction conditions.

Keys to controlling the polymerization reaction may include (1) matching the reactivity of the groups in the

5 N
BB
11

10 initiator (R^{11} , R^{12} and R^{13}) with the group(s) on the monomer (R^1 - R^4), and (2) matching the energetics of bond breaking and bond forming in dormant species (e.g., dormant polymer chains) and transition metal species (as discussed elsewhere in the specification). Matching the reactivities of the initiator with the monomer depends to some degree on the radical stabilizing effects of the substituents. Thus, where the monomer is a simple alkene or halogenated alkene (e.g., ethylene, propylene, vinyl chloride, etc.), one may select an alkyl halide initiator (e.g., where two or three of R^{11} , R^{12} and R^{13} are C_1 - C_6 alkyl). On the other hand, if one wishes to polymerize an arene- or ester-stabilized monomer (e.g., a (meth)acrylate, acrylonitrile or styrene), one may select an initiator which is stabilized by a similar group (wherein one of R^{11} , R^{12} and R^{13} is aryl, heterocyclyl, alkoxy carbonyl, CN, carboxyamido [$C(=O)NR^6R^7$], etc.). Such "matching" of substituents on the initiator and monomer provides a beneficial balance of the relative reactivities of the initiator and monomer.

20 Preferably, the monomer, initiator, transition metal compound and ligand are selected such that the rate of initiation is not less than 1,000 times (preferably not less than 100 times) slower than the rate of propagation and/or transfer of the X group to the polymer radical. (In the present application, "propagation" refers to the reaction of a


25

polymer radical with a monomer to form a polymer-monomer adduct radical.)

5
BB
10
15
20
25
The present polymerization may be conducted in bulk, in the gas phase (e.g., by passing the monomer in the gas phase over a bed of the catalyst which has been previously contacted with the initiator and ligand), in a sealed vessel or in an autoclave. Polymerizing may be conducted at a temperature of from -78° to 200° , preferably from 0° to 160° and most preferably from 80° to 140° . The reaction should be conducted for a length of time sufficient to convert at least 10% (preferably at least 50%, more preferably at least 75% and most preferably at least 90%) of the monomer to polymer. Typically, the reaction time will be from several minutes to 5 days, preferably from 30 minutes to 3 days, and most preferably from 1 to 24 hours. Polymerizing may be conducted at a pressure of from 0.1 to 100 atmospheres, preferably from 1 to 50 atmospheres and most preferably from 1 to 10 atmospheres (although the pressure may not be measurable directly if conducted in a sealed vessel).

One may also conduct a "reverse" ATRP, in which the transition metal compound is in its oxidized state, and the polymerization is initiated by, for example, a radical initiator such as azobis(isobutyronitrile) ("AIBN"), a peroxide such as benzoyl peroxide (BPO) or a peroxy acid such as peroxyacetic acid or peroxybenzoic acid. The radical

initiator is believed to initiate "reverse" ATRP in the following fashion:



where "I" is the initiator, $M_t^nX_{n-1}$ is the transition metal compound, M is the monomer, and I-M-X and $M_t^nX_{n-1}$ participate in "conventional" or "forward" ATRP in the manner described above.

After the polymerizing step is complete, the formed polymer is isolated. The isolating step of the present process is conducted by known procedures, and may comprise precipitating in a suitable solvent, filtering the precipitated polymer, washing the polymer and drying the polymer.

Precipitation can be typically conducted using a suitable C_5 - C_8 -alkane or C_5 - C_8 -cycloalkane solvent, such as pentane, hexane, heptane, cyclohexane or mineral spirits, or using a C_1 - C_6 -alcohol, such as methanol, ethanol or isopropanol, or any mixture of suitable solvents. Preferably, the solvent for precipitating is hexane, mixtures of hexanes, or methanol.

RECEIVED "ATHEOEO"

5/11/11
BBI

5

030316Z

15

20

25

or random copolymers of styrene and a (meth)acrylate or acrylonitrile may be useful thermoplastic elastomers having high solvent resistance.

5 Furthermore, block copolymers in which the blocks alternate between polar monomers and non-polar monomers produced by the present invention are useful amphiphilic surfactants or dispersants for making highly uniform polymer blends. Star polymers produced by the present process are useful high-impact (co)polymers. (For example, STYROLUX™, and anionically-polymerized styrene-butadiene star block copolymer, is a known, useful high-impact copolymer.)

10 The (co)polymers of the present invention may have a number average molecular weight of from 1,000 to 500,000 g/mol, preferably of from 2,000 to 250,000 g/mol, and more preferably of from 3,000 to 200,000 g/mol. When produced in bulk, the number average molecular weight may be up to 1,000,000 (with the same minimum weights as mentioned above). The number average molecular weight may be determined by size exclusion chromatography (SEC) or, when the initiator has a group which can be easily distinguished from the monomer(s) by NMR spectroscopy (e.g., when 1-phenylethyl chloride is the initiator and methyl methacrylate is the monomer).

20 Thus, the present invention also encompasses novel block, multi-block, star, gradient, random hyperbranched and dendritic copolymers, as well as graft or "comb" copolymers.

5N
BB
10
15
20
25
"SECRET"

SECRET

10


15

20

25

simply add successive monomers to form successive blocks. Further, it is also possible (and in some cases advantageous) to first isolate a (co)polymer produced by the present ATRP process, then react the polymer with an additional monomer using a different initiator/catalyst system (to "match" the reactivity of the growing polymer chain with the new monomer). In such a case, the product polymer acts as the new initiator for the further polymerization of the additional monomer.

Thus, the present invention also encompasses block copolymers of the formula:






wherein R^{11} , R^{12} , R^{13} and X are as defined above; M^1 , M^2 , M^3 , ... up to M^u are each a radically polymerizable monomer (as defined above) selected such that the monomers in adjacent blocks are not identical (although monomers in non-adjacent blocks may be identical) and p , q , r , ... up to s are independently selected such that the number average molecular weight of each block is from 1,000 to 250,000 g/mol. After an appropriate end group conversion reaction (conducted in accordance with known methods), X may also be, for example, H , OH , N_3 , NH_2 , $COOH$ or $CONH_2$.

SECRET/ATHE060


5
N
B
B
1

Where the $R^{11}R^{12}R^{13}C$ group of the initiator contains a second "X" group, the block copolymers may have one of the following formulas:



wherein R^{11} , R^{12} , R^{13} , X, M^1 , M^2 , M^3 , ... up to M^u , and p, q, r, ... up to s are as defined above.


The present invention is also useful for making essentially random copolymers. By "essentially random" copolymers, the copolymers are as close to statistically random as is possible under radical polymerization conditions. The present ATRP process is particularly useful for producing random copolymers where one of the monomers has one or two bulky substituents (e.g., 1,1-diarylethylene, didehydromalonate C_1 - C_{20} diesters, C_1 - C_{20} diesters of maleic or fumaric acid, maleic anhydride and/or maleic diimides [where Y is NR^8 as defined above], etc.), from which homopolymers may be difficult to prepare, due to steric considerations. Thus, the present invention also concerns a random copolymer of the formula:



or


RECEIVED "LATE"

5
B
B
B



where R^{11} , R^{12} , R^{13} and X are as defined for the block copolymer above, M^1 and M^2 are different radically-polymerizable monomers (as defined above), and M^v is one of M^1 and M^2 and M^v is the other of M^1 and M^2 . However, p , q , r , ... up to s are independently selected such that the number average molecular weight of the copolymer is from 1,000 to 1,000,000 g/mol, preferably from 2,000 to 250,000, and more preferably from 3,000 to 150,000 g/mol. The ratio of (1) the total number of "blocks" of statistically random units to (2) the total number of monomer units is preferably at least 1:5, more preferably at least 1:8, and most preferably at least 1:10. The present random copolymer can also serve as a block in any of the present block copolymers.

Preferably, at least one of M^1 and M^2 has the formula:







wherein at least one of R^1 and R^2 is CN, CF_3 , straight or branched alkyl of from 4 to 20 carbon atoms (preferably from 4 to 10 carbon atoms, more preferably from 4 to 8 carbon atoms), C_3-C_8 cycloalkyl, aryl, heterocyclyl, $C(=Y)R^5$, $C(=Y)NR^6R^7$ and $YC(=Y)R^8$, where aryl, heterocyclyl, Y , R^5 , R^6 , R^7 and R^8 are as defined above; and

R³ and R⁴ are as defined above; or

R¹ and R³ are joined to form a group of the formula C(=O)-Y-C(=O), where Y is as defined above.

More preferred monomers for the present include styrene,
5 acrylonitrile, C₁-C₄ esters of (meth)acrylic acid and 1,1-diphenylethylene.

5N
BB
10 The present invention is also useful for forming so-called "star" polymers and copolymers. Thus, where the initiator has three or more "X" groups, each of the "X" groups can serve as a polymerization initiation site. Thus, the present invention also encompasses star (co)polymers of the formula:



15 where R^{11'}, R^{12'} and R^{13'} are the same as R¹¹, R¹² and R¹³ with the proviso that R^{11'}, R^{12'} and R^{13'} combined contain from 2 to 5 X groups; X is as defined for the block copolymer above; M¹, M²,
20 M³, ... M^u are as defined above for the present block copolymers; and z is from 3 to 6.

Initiator suitable for use in preparing the present star (co)polymers are those in which the R¹¹R¹²R¹³C group possesses at least two substituents which can be "X" (as defined above).


Preferably, these substituents are identical to "X". Examples of such initiators include chloroform, carbon tetrachloride, [insert examples from above]. Preferred initiators of this type include 2,2-bis(chloromethyl)-1,3-dichloropropane, 2,2-bis(bromomethyl)-1,3-dibromopropane), $\alpha, \alpha', \alpha''$ -trichloro- and $\alpha, \alpha', \alpha''$ -tribromocumene and hexakis(α -chloro- and α -bromomethyl)benzene), the most preferred being hexakis(α -bromomethyl)benzene.

In the present copolymers, each of the blocks may have a number average molecular weight in accordance with the homopolymers described above. Thus, the present copolymers may have a molecular weight which corresponds to the number of blocks (or in the case of star polymers, the number of branches times the number of blocks) times the number average molecular weight range for each block.

The present invention also encompasses graft or "comb" copolymers, prepared by sequential ATRP's. Thus, a (co)polymer is produced by a first ATRP, in which at least one of the monomers has a R^1-R^4 substituent which is encompassed by the description of the "X" group above. Preferably this substituent is Cl or Br. Examples of preferred monomers would thus include vinyl chloride, 1- or 2- chloropropene, vinyl bromide, 1,1- or 1,2-dichloro- or dibromoethene, trichloro- or tribromoethylene, tetrachloro- or tetrabromoethylene, chloroprene, 1-chlorobutadiene, 1- or 2-bromodutadiene, etc. More preferred monomers include vinyl chloride, vinyl bromide

and chloroprene. It may be necessary to hydrogenate (by known methods) a (co)polymer produced in the first ATRP of chloroprene prior to the second ATRP, using the polymer produced by the first ATRP as the initiator.

5 Gradient or tapered copolymers can be produced using ATRP by controlling the proportion of two or more monomers being added. For example, one can prepare a first block (or a oligomer) of a first monomer, then a mixture of the first monomer and a second, distinct monomer can be added in proportions of from, for example, 1:1 to 9:1 of first monomer to second monomer. After conversion of all monomer(s) is complete, sequential additions of first monomer-second monomers mixtures can provide subsequent "blocks" in which the proportions of first monomer to second monomer vary. Thus, 15 the present invention also encompasses a copolymer of the formula:



20 where R^{11} , R^{12} , R^{13} and X are as defined for the block copolymer above, M^1 and M^2 are different radically-polymerizable monomers (as defined above), and a , b , c , d , e , f ,... up to g and h are non-negative numbers independently selected such that $a + b = c + d = 100$, and any or all of $(e + f)$, $(g + h)$ and $(i + j) = 100$ or 0, wherein the $a:b$ ratio is from 100:0 to 0:100, the $c:d$ ratio is from 95:5 to 5:95 (preferably from 90:10 to

5
 10
 15
 20
 25
 30
 35
 40
 45
 50
 55
 60
 65
 70
 75
 80
 85
 90
 95
 100

10:90), such that $c < a$ and $d > b$, and where applicable, the
e:f ratio is from 90:10 to 10:90 (preferably from 80:20 to
20:80), such that $e < c$ and $f > d$, and depending on the number
of blocks, the endpoints of the molar ratio ranges of first
monomer to second monomer in successive blocks may
progressively decrease or increase by 5 (preferably by 10)
such that the e:f ratio is from 5:95 to 95:5 (preferably from
10:90 to 90:10), such that $e \neq c$ and $f \neq d$, and the i:j ratio
is from 0:100 to 100:0, such that $i \neq e$ and $j \neq f$.

Preferably, the proportions of first and second monomers
in subsequent "blocks" vary by at least 10% (e.g., $c = a \pm 10$
and $b = d \pm 10$), preferably by at least 20%, up to 50%, from
the preceding block. In a further embodiment, the relative
proportions of first monomer to second monomer can be
controlled in a continuous manner, using for example a
programmable syringe or feedstock supply pump.

When either the initiator or monomer contains a
substituent bearing a remote (i.e., unconjugated) ethylene or
acetylene moiety, ATRP can be used to prepare cross-linked
polymers and copolymers.

Polymers and copolymers produced by the present process
have surprisingly low polydispersity for (co)polymers produced
by radical polymerization. Typically, the ratio of the weight
average molecular weight to number average molecular weight
("M_w/M_n") is ≤ 1.5 , preferably ≤ 1.4 , and can be as low as 1.10
or less.

Because the "living" (co)polymer chains retain an initiator fragment including X or X' as an end group, or in one embodiment, as a substituent in a monomeric unit of the polymer chain, they may be considered end-functional or in-chain functional (co)polymers. Such (co)polymers may be used directly or be converted to other functional groups for further reactions, including crosslinking, chain extension, reactive injection molding (RIM), and preparation of other types of polymers (such as polyurethanes, polyimides, etc.).

The present invention provides the following advantages:

- A larger number and wider variety of monomers can be polymerized by radical polymerization, relative to ionic and other chain polymerizations;
- Polymers and copolymers produced by the present process exhibit a low polydispersity (e.g., $M_w/M_n \leq 1.5$, preferably ≤ 1.4 , more preferably ≤ 1.25 , and most preferably, ≤ 1.10), thus ensuring a greater degree of uniformity in the (co)polymer properties;
- One can select an initiator which provides an end group having the same structure as the repeating polymer units (1-phenylethyl chloride as initiator and styrene as monomer);
- The present process provides high conversion of monomer and high initiator efficiency;
- The present process exhibits excellent "living" character, thus facilitating the preparation of

- block copolymers which cannot be prepared by ionic processes;
- Polymers produced by the present process are well-defined and highly uniform, comparable to polymers produced by living ionic polymerization;
 - End-functional initiators (e.g., containing COOH, OH, NO₂, etc., groups) can be used to provide an end-functional polymer in one pot;
 - The end functionality of the (co)polymers produced by the present process (e.g., Cl, Br, I, CN, CO₂R) can be easily converted to other functional groups (e.g., Cl, Br and I can be converted to OH or NH₂ by known processes, and CN or CO₂R can be hydrolyzed to form a carboxylic acid by known processes), thus facilitating their use in chain extension processes (e.g., to form long-chain polyamides, polyurethanes and/or polyesters); and
 - In some cases (e.g., where "X" is Cl, Br and I), the end functionality of the polymers produced by the present process can be reduced by known methods to provide end groups having the same structure as the repeating polymer units.

Hereinbelow, studies conducted by the present Inventors on ATRP to investigate the various parameters which affect ATRP will be described. Exemplary experimental protocols will follow.

A number of commercially available alkyl halides, R-X, combined with Cu(I)X'/Bpy, where X = X' = Cl or Br, can be used as efficient model initiator systems for the atom transfer radical polymerization (ATRP) of styrene, (meth)acrylates and other radically polymerizable monomers. The effects of various parameters in ATRP will be discussed hereinbelow to provide guidance as to the efficient control of radical polymerization.

Atom Transfer Radical Polymerization of Styrene and (Meth)acrylates Initiated with an Alkyl Halide, R-X, and in the Presence of CuX', Complexed by 2,2'-Bipyridine. Using 1-phenylethyl chloride (hereinafter "1-PECl") as an initiator, one molar equivalent of Cu(I)Cl as a catalyst, and three molar equivalents of 2,2'-bipyridine (hereinafter "Bpy") as a ligand (both equivalents of catalyst and ligand being relative to 1-PECl) in a model system, the so-called atom transfer radical polymerization (ATRP) of styrene (hereinafter "St") proceeds in a "living" fashion at 130°C. Similarly, using various 1:1:3 R-X:CuX':Bpy initiator systems, the atom transfer radical polymerization of styrene and various (meth)acrylates at different temperatures also affords the product polymers with the predicted molecular weight (up to $M_n > 10^5$), having excellent low polydispersity (as low as 1.15; see Table 1 below).

TABLE 1

Characterization Data for ATRP of Styrene and Various (Meth)acrylates
Initiated with RX/CuX'/Bpy^a

Monomer	RX ^b /CuX'	T (°C)	M _{n, th} ^c	M _{n, SEC}	M _w /M _n
Styrene	1-PECl/CuCl	130	120,000	110,500	1.45
		100	97,000	93,300	1.50
	1-PEBr/CuBr	80	8,300	8,000	1.25
MA	2-EPNCl/CuCl	130	30,500	31,000	1.40
	2-EPNBr/CuBr	80	19,100	21,500	1.25
	2-MPNBr/CuBr	100	27,500	29,000	1.15
	α, α' -Br ₂ -xylene/ CuBr	100	29,500	31,000	1.25
BuA ^d	2-MPNBr/CuBr	130	15,000	13,500	1.50
MMA ^d	2-EiBBBr/CuBr	100	10,000	9,800	1.40

^amolar ratio of RX/CuX'/Bpy = 1/1/3; ^b1-PECl: 1-phenylethyl chloride, 1-PEBr: 1-phenylethyl bromide, 2-EPNCl: ethyl 2-chloropropionate, 2-EPNBr: ethyl 2-bromopropionate, 2-MPNBr: methyl 2-bromopropionate, 2-EiBBBr: ethyl 2-bromoisobutyrate; ^ccalculated according to eq. 1; ^d in ethyl acetate solution, 50% by volume.

As an illustrative example of the controlled character of the ATRP of (meth)acrylic esters, Figure 3 presents the kinetics of methyl acrylate ("MA") bulk polymerization at 130°C, initiated with 1-PECl in the presence of Cu(I)Cl (1 equiv.) and Bpy (3 equiv.). The straight semilogarithmic kinetic plot of $\ln([M]_0/[M])$ vs. time ("t", in minutes) indicates that the concentration of growing radicals is constant, and that termination reactions are minimal.

Moreover, the experimental molecular weight, $M_{n,SEC}$, increases with monomer conversion (Figure 4) and matches the theoretical molecular weight, $M_{n,th}$ (Figure 5), as calculated by eq. 1:

$$M_n = (\Delta[M] / [R-X]_0) \times (MW)_0 \quad (1)$$

where $\Delta[M]$ represents the concentration of consumed monomer MA, $[R-X]_0$ represents the initial concentration of 1-PECl, and $(MW)_0$ represents the molecular weight of MA. These results provide evidence that 1-PECl acts as an efficient initiator, and that the number of active chains remains practically unchanged during the MA polymerization. Thus, termination and transfer side reactions, if they exist, are not significant. Both of these results suggest that the ATRP of MA is a "living" process.

Furthermore, a series of bulk ATRP's of MA was carried out at 130°C, using various monomer/initiator molar ratios,

[MA]₀/[1-PECl]₀, and a constant ligand/catalyst/initiator molar ratio of 3/1/1. Figure 6 shows the correlation of the experimental molecular weights, $M_{n,SEC}$, with the theoretical molecular weights, $M_{n,th.}$, calculated by eq. (1). A linear plot is obtained in the molecular weight range of from 1.5×10^3 to 1.35×10^5 . The slope of the straight line is 0.95, thus indicating a high initiator efficiency. These results again support a "living" process of MA polymerization initiated with 1:1:3 1-PECl:CuCl:Bpy.

End Group Analysis of Polymers Obtained by Atom Transfer Radical Polymerization. The nature of the chain ends of low molecular weight polystyrene synthesized by the ATRP technique was analyzed by means of ¹H NMR spectroscopy. Figure 7 presents the ¹H NMR spectra of PSt which was prepared at 130°C using 2-chloropropionitrile as an initiator, in the presence of one molar equiv. of CuCl and 3 molar equiv. of Bpy. Two broad signals at 4.2-4.4 ppm are assigned to two different stereoisomers (*m* and *r*) of end group *a* in the anticipated structure 1. Moreover, two additional broad bands at 0.85 and 0.96 ppm in Figure 7 represent two stereoisomers (*m* and *r*) of the end group *d*.

Comparison of the integration values for the two end group resonances in the ¹H NMR spectrum (Figure 7) shows a 3:1 molar ratio of *a* and *d*. This may suggest that the St polymerization was initiated with 2-propionitrile radicals and

was efficiently deactivated with an equimolar amount of chlorine atoms (relative to the 1-propionitrile group). Moreover, comparison of the integration of the end groups with phenyl groups, *e*, at 6.5 ppm to 7.3 ppm, and to other groups, *b* and *c*, in the backbone of the polystyrene chain at 1.2 ppm to 2.5 ppm gave a molecular weight similar to the one obtained from the SEC measurement ($M_{n,NMR} \sim 2000$ vs. $M_{n,SEC} \sim 2100$), indicating a quantitative initiation by 2-chloropropionitrile. This result shows a high initiator efficiency in ATRP.

Stereochemistry of Atom Transfer Radical Polymerization.

To better understand the mechanism of ATRP, the stereochemistry of MMA polymerization was investigated.


The tacticity of poly(methyl methacrylate), PMMA, was calculated from the ^{13}C NMR of the C=O group and the quaternary carbon atom, and from the ^1H NMR of the α -methyl group. The ^{13}C NMR resonances of the C=O group and the quaternary carbon atom are recorded in the regions 175-179 ppm and 44-46.5 ppm, respectively, with respect to the reference peak of CDCl_3 at 77.2 ppm. The assignment of the ^{13}C signals was performed to Peat and Reynolds (see Bamford, *Reactivity, Mechanism and Structure in Polymer Chemistry*, Jenkins, A. D. and Ledwith, A., eds, John Wiley & Sons, London (1974), p. 52; and Peat et al, *Tetrahedron Lett.*, **1972**, 14, 1359).

Figure 8A displays the ^{13}C NMR spectra of the C=O group and the quaternary carbon atom of PMMA prepared at 100°C using

methy1 2-bromoisobutyrate ("2-MiBBr"), CuBr and Bpy in a 1/1/3 molar ratio, and Figure 8B displays the ^{13}C NMR spectra of the C=O group and the quaternary carbon atom of PMMA prepared using a classic radical initiator, AIBN. Both spectra are almost identical. Indeed, up to a pentad sequence, PMMAs prepared using a classic radical initiator such as AIBN or BPO and various ATRP initiator systems have the same compositions, within the limits of experimental error (see Table 2 below). Moreover, the stereochemistry for PMMA prepared by ATRP appears to be consistent with a Bernoullian process, as indicated by a ρ value of ~ 1 . These results indicate the presence of the same type of active species in the present Cu(I)X'-catalyzed polymerization and in conventional free radical polymerization. The similarities in stereochemistry and regiochemistry observed in the present results are consistent with the results observed in Bu_3SnH -mediated radical cyclizations and in Cu(I)-catalyzed chlorine transfer cyclizations reported by others (see (a) Bellus, D. *Pure & Appl. Chem.* **1985**, 57, 1827; (b) Nagashima, H.; Ozaki, N.; Ishii, M.; Seki, K.; Washiyama, M.; Itoh, K. *J. Org. Chem.* **1993**, 58, 464; (c) Udding, J. H.; Tuijp, K. J. M.; van Zanden, M. N. A.; Hiemstra, H.; Speckamp, W. N. *J. Org. Chem.* **1994**, 59, 1993; (c) Seijas et al, *Tetrahedron*, **1992**, 48(9), 1637).

Effect of the Structure of the Initiator on Atom Transfer Radical Polymerization. Table 3 reports the data for the ATRP

of styrene at 130°C using various commercially available alkyl chlorides, Cu(I)Cl (1 molar equiv.) and Bpy (3 molar equiv.)



06000" 2874060

Table 2

Comparison of Fractions of Pentads, Triads, and Diads in Poly(methyl methacrylate) (PMMA) Prepared Using Classic Initiators and Various ATRP Initiator Systems

T (°C)	Initiator system	mmmm	mmmr	mmrr	rmrm + mrrm	rmrr + mrrr	rrmm	rrrr	rrrr	mm	mr	rr	m	r	ρ^a
130	1-PECL/CuCl/Bpy ^b	--	--	--	--	--	--	--	--	0.06	0.38	0.56	0.25	0.75	0.99
	BPO ^c	--	--	--	--	--	--	--	--	0.06	0.37	0.55	0.245	0.755	1.00
100	2-EiBBR/CuBr/Bpy ^d	0.01	0.03	0.04	0.11	0.26	0.06	0.22	0.27	0.05	0.36	0.59	0.23	0.77	1.04
	AIBN ^e	0.02	0.03	0.04	0.11	0.27	0.04	0.21	0.28	0.06	0.34	0.60	0.23	0.77	1.04
60	2-EiBBR/CuBr/Bpy ^d	--	--	--	--	--	--	--	--	0.04	0.33	0.63	0.205	0.795	0.99
	AIBN ^f	--	--	--	--	--	--	--	--	0.03	0.35	0.62	0.205	0.795	0.94

^a The persistence ratio: $\rho = 2(m)(r)/(mr)$; ^b Polymerization conditions: $[MMA]_0 = 9.36$ M, $[1-PECL]_0 = 0.11$ M, $[1-PECL]_0/[CuCl]_0/[Bpy]_0 = 1/1/3$; ^c Polymerization conditions: $[MMA]_0 = 9.36$ M, $[BPO] = 0.1$ M; ^d Polymerization conditions: $[2-EiBBR]_0 = 0.055$ M, $[1-PECL]_0/[CuCl]_0/[Bpy]_0 = 1/1/3$; ^e Polymerization conditions: $[MMA]_0 = 9.36$ M, $[AIBN] = 0.1$ M; ^f Hatada, K. et al, *Polym. J.* 1987, 19, 413.

as initiator, catalyst, and ligand, respectively. Initiators which possess either inductive or resonance- stabilizing substituents (e.g., two or more halogen atoms in addition to the Cl transfer atom, CN, COOR, and/or aryl [Ph]) can serve as efficient mono- or bi- functional initiators (i.e, providing high initiator efficiency ["f" > 0.9] and narrow molecular weight distribution [e.g., $M_w/M_n \sim 1.25-1.5$]).

In contrast, simple alkyl chlorides as butyl chloride, C_4H_9Cl , and dichloromethane, CH_2Cl_2 , do not work well with St, giving uncontrolled polymers with unexpectedly high molecular weights and broad molecular weight distribution. These results are very similar to those obtained under similar conditions in the absence of initiator (see Table 3 below). These results indicate very poor efficiency of C_4H_9Cl and CH_2Cl_2 as initiators for the ATRP of St.

The results shown in Table 3 may be tentatively correlated with the carbon-halide bond strength or bond dissociation energy (BDE). For initiators having a high BDE, such as C_4H_9Cl and CH_2Cl_2 (see Wang et al, *Macromolecules*, **1993**, *26*, 5984; and Baumgarten et al, *Macromolecules*, **1991**, *24*, 353), the chloride atom transfer from the initiator to $Cu(I)Cl$ appears to be very difficult because of the strong carbon-chlorine bonds. Introduction of an inductive or resonance-stabilizing substituent into the initiator reduces the BDE of the C-Cl bond (Wang et al and Baumgarten et al, *supra*), and the generation of initiating radicals by chlorine atom

transfer becomes facile and efficient, resulting in a high initiator efficiency and narrow MWD in the ATRP of St.

TABLE 3

Styrene ATRP, Using Various Initiators in the Presence of CuCl (1 molar equiv.) and Bpy (3 molar equiv.)^a

Initiator	[In*] ₀ (10 ³ M)	M _{n,th} ^b	M _{n,SEC}	M _w /M _n
-	-	-	134,700	1.95
C ₄ H ₉ Cl	0.082	10,000	111,500	1.75
CH ₂ Cl ₂	0.085	9,700	129,000	2.20
CHCl ₃	0.040	20,500	21,900	1.45
CCl ₄	0.047	17,600	15,500	1.30
CH ₃ CH(Cl)CN	0.037	22,300	22,400	1.35
CH ₃ CH(Cl)CN	0.35	2,280	2,100	1.25
CH ₃ CH(Cl)COOC ₂ H ₅	0.038	21,500	20,000	1.45
CH ₃ CH(Cl)COOC ₂ H ₅	0.65	1,210	1,290	1.35
C ₆ H ₅ CH ₂ Cl	0.075	11,000	10,600	1.45
ClCH ₂ C ₆ H ₄ CH ₂ Cl	0.12	6,890	6,600	1.45

^a Conversion of the polymerization: 90%-100%

^b calculated based on eq. 1

In*: Initiator

It must be pointed out here that the same conclusions are observed for ATRP of other monomers, such as MA and MMA.

Effect of the Polymer Structure, M_n , and the Polymeric Halide, M_n-X' , on Atom Transfer Radical Polymerization. Figure 9 illustrates the kinetic plots of the ATRP of three typical monomers, St, MA, and MMA, using the same initiator system 1-PEC1/CuCl/Bpy (1/1/3), under the same experimental conditions, in bulk and at 130°C.

The slopes of the straight kinetic plots in Figure 9 allow the calculation of the apparent propagation rate constants (k_p^{app}) in the ATRP of St, MA and MMA. Furthermore, knowing the corresponding thermodynamic parameters, A_p and E_p , one can estimate the absolute propagation rate constants at various temperatures, k_p' , and the stationary concentrations of growing radicals, $[P']_{st}$, according to equations (5) and (6), respectively:

$$R_p = -d[M]/dt = k_p' \times [M] \times [P']_{st} \quad (2)$$

For each system described herein, $[P']_{st}$ can be considered constant. Therefore:

$$-d[M]/dt = k_p' \times [M] \times [P']_{st} = k_p^{app} \times [M] \quad (3)$$

and

$$\ln([M]_0/[M]) = k_p^{app} \times t \quad (4)$$

$$\ln(k_p') = \ln(A_p) - (E_p/RT) \quad (5)$$

$$[P']_{st} = k_p^{app}/k_p' \quad (6)$$

Table 4 shows the kinetic data and estimated concentrations of growing radicals in bulk ATRP of St, MMA, and MA initiated with 1-PECl/CuCl/Bpy (1/1/3) at 130°C. The concentration of growing radicals decreases in the order $[P']_{MMA} > [P']_{St} \approx [P']_{MA}$.

TABLE 4

Kinetic Data and Estimated Concentration of Growing Radicals $[P']$, for Bulk ATRP of St, MA, and MMA Initiated with 1-PECl/CuCl/Bpy (1/1/3) at 130°C

Monomer	MA	MMA	St
$[1-PECl]_0$ (mol/l)	0.038	0.038	0.038
$[M]_0$ (mol/l)	11.1	9.36	8.7
k_p' , 130°C (10^3 mol/l s ⁻¹)	14.1 ^a	3.17 ^b	6.87 ^c
k_p^{app} , 130°C (10^{-4} s ⁻¹)	3.14	5.83	1.35
$[P']$ (10^{-7} M)	0.22	1.84	0.19

^a: $\ln k_{p,MA} = 18.42 - (3574/T)$, see Odian, G. *Principles of Polymerization*, Wiley-Interscience, New York, 1991;

^b: $\ln k_{p,MMA} = 14.685 - (2669/T)$, see Hutchinson et al,

Macromolecules, **1993**, 26, 6410; ^c: $\ln k_{p,St} = 16.786 - (3204/T)$, see Hutchinson et al, *supra*.

Effect of the Transfer Atom (Leaving Group), X' , on Atom Transfer Radical Polymerization. Since the atom transfer process reflects the strength of the bond breaking and bond forming in M_n-X' , it is expected that the leaving group, X' , will strongly affect control of the atom transfer reaction.

From Table 5, it can be noted that ATRP is essentially faster when X is bromine as compared to when X is chlorine. This can be explained by the presence of more growing radicals in the polymerization process when X is bromine as compared to when X is chlorine.

The effect of the leaving group, X , on the living character of the polymerization is also significant. For instance, in MA polymerizations at 100°C using the same molar ratio of initiator/ CuX /Bpy and the same initiating radical, ethyl propionate, at high monomer conversions (e.g., > 50%) the experimental molecular weight, $M_{n,SEC}$, and is very close to the theoretical molecular weight, $M_{n,th}$, when $X = X' =$ either Br or Cl. However, at relatively low conversions (e.g., < 50%), the discrepancy between $M_{n,SEC}$ and $M_{n,th}$ is much larger when $X = X' = Cl$ ("Cl ATRP") as compared to when $X = X' = Br$ ("Br ATRP") (see Figures 10 and 11).

Moreover, the polydispersity of resulting polymers obtained by Cl ATRP is usually larger than the polydispersity obtained by Br ATRP (e.g., an M_w/M_n of 1.15-1.35 vs. 1.30-1.50; see Figures 10 and 11).

Table 5
The Effect of the Leaving Group, X, on Kinetics
of ATRP at Different Temperatures^a

Monomer	T, °C	ATRP	k_p^{app}	k_p^*	$[P^*]$
			$10^{-5} s^{-1}$	$10^3 mol/l$	$10^{-9} mol/l$
MMA	80	Cl ATRP	~ 1.71	1.24	13.8
		Br ATRP	~ 3.52	1.24	28.4
MA	80	Cl ATRP	b	4.01	-
		Br ATRP	~ 1.28	4.01	3.19
	100	Cl ATRP	1.45	6.89	2.10
		Br ATRP	3.47	6.89	5.02
St	80	Cl ATRP	b	2.23	-
		Br ATRP	~ 1.45	2.23	6.50

^a 1 - PCl and 1 - PBr were used as Initiators for Cl and Br ATRP, respectively, $[1 - PEX]_0 = 0.1M$, and $[1 - PEX]_0 / [CuX]_0 / [Bpy]_0 = 1 / 1 / 3$; b no polymer can be detected in 40 hrs.

090344B7 030396

Effect of the Concentrations of the Components in Initiator System, R-X/CuX/Bpy, on Atom Transfer Radical Polymerization. In order to gain a better understanding of the ATRP mechanism, the effects of the components in the initiator system compositions on the kinetics and the living character of polymerization were investigated.

As discussed in the previous sections, the slope of the kinetic semilogarithmic anamorphoses allows the calculation of apparent rate constant k_p^{app} , and thus the external orders in initiator, catalyst, and ligand, can be determined:

$$k_p^{app} = d(\ln[M])/dt = k[RX]_0^x \times [CuX]_0^y \times [Bpy]_0^z \quad (7)$$

and

$$\ln(k_p^{app}) = \ln(k) + x\ln([RX]_0) + y\ln([CuX]_0) + z\ln([Bpy]_0) \quad (8)$$

The plots of $\ln(k_p^{app})$ vs. $\ln([1-PECl]_0)$, $\ln(k_p^{app})$ vs. $\ln([CuCl]_0)$, and $\ln(k_p^{app})$ vs. $\ln([Bpy]_0)$ for St ATRP in bulk at 130°C are given in Figures 12A-C. The fraction orders observed in these graphs are approximately 1, 0.4, and 0.6 for $[1-PECl]_0$, $[CuCl]_0$, and $[Bpy]_0$, respectively. The first order of k_p^{app} in initiator, $[1-PECl]_0$, is expected. However, since the systems studied were heterogenous, it is difficult to give precise physical meanings for 0.4 and 0.6 orders in $[CuCl]_0$ and $[Bpy]_0$, respectively.

5 The effects of the compositions of the components in
initiator system on the living character of the above-
described ATRP of St reveal several important features. As
seen from Figure 13, there appear to be no significant effects
of $[\text{CuCl}]_0$ on the initiator efficiency and the molecular weight
distribution. Indeed, even in the presence of 0.3 molar
equiv. of CuCl relative to 1- PECl , the experimental molecular
weight, $M_{n,\text{SEC}}$, still linearly increases with monomer conversion
and is close to the theoretical molecular weight obtained by
means of eq. 1 (Figure 13A). The similar results are also
found for MA (Figures 5 and 14). These findings suggest that
in ATRP, the CuX acts as a catalyst and the addition of
catalytic amount of CuX complexed by Bpy is sufficient to
promote a controlled ATRP, even in these heterogeneous
15 systems.

**Transition Metal Catalyzed-Atom Transfer Radical Addition
and Transition Metal Catalyzed-Atom Transfer Radical
Polymerization.** As described above, atom transfer radical
polymerization, ATRP, can be considered as a succession of
consecutive atom transfer radical additions, ATRA's. The
prerequisite for a successful transformation of transition
metal catalyzed-ATRA to transition metal catalyzed-ATRP is
that a number of polymeric halides, $M_n\text{-X}$, can be effectively
activated by M_t^n (Fig. 2). Present work demonstrates that a
20

Cu(I)/Cu(II)-based redox process in the presence of Bpy can achieve that goal.

Indeed, to prevent possible polymerization and to obtain the monomeric adduct, R-M-X, in good to excellent yields in the ATRA process, organic chemists often use either (1) activated organic halogens as radical sources, (2) terminal alkenes without resonance-stabilizing substituents or (3) both activated organic halogens as radical sources and terminal alkenes without resonance-stabilizing substituents (see (a) Bellus, D. *Pure & Appl. Chem.* **1985**, 57, 1827; (b) Nagashima, H.; Ozaki, N.; Ishii, M.; Seki, K.; Washiyama, M.; Itoh, K. *J. Org. Chem.* **1993**, 58, 464; (c) Udding, J. H.; Tuijp, K. J. M.; van Zanden, M. N. A.; Hiemstra, H.; Speckamp, W. N. *J. Org. Chem.* **1994**, 59, 1993; (c) Seijas et al, *Tetrahedron*, **1992**, 48(9), 1637; (d) Nagashima, H.; Wakamatsu, H.; Ozaki, N.; Ishii, T.; Watanabe, M.; Tajima, T.; Itoh, K. *J. Org. Chem.* **1992**, 57, 1682; (e) Hayes, T. K.; Villani, R.; Weinreb, S. M. *J. Am. Chem. Soc.* **1988**, 110, 5533; (f) Hirao et al, *Syn. Lett.*, **1990**, 217; and (g) Hirao et al, *J. Synth. Org. Chem. (Japan)*, **1994**, 52(3), 197; (h) Iqbal, J; Bhatia, B.; Nayyar, N. K. *Chem. Rev.*, **94**, 519 (1994)). Under such conditions, the further generation of free radicals, R-M \cdot , is kinetically less favorable, since R-M-X is much less reactive than R-Y towards the transition metal species, M $_t^n$ (Fig. 1).

From the results described herein, the following parameters appear to be important to promote the successful

transformation of ATRA to ATRP. First, the use of suitable ligands (e.g., Bpy, $P(OEt)_3$) increases the solubility of the transition metal compound (e.g., CuX) by coordination, can facilitate the abstraction of a halogen atom from the initiator, and more importantly, can facilitate abstraction of the transfer atom or group from the dormant polymeric halide, $R-M_n-X$, with the formation of initiating and growing radicals (Fig. 2). Secondly, as demonstrated in Table 3, the presence of either inductive or resonance stabilizing substituents in the initiator are beneficial for generating initiating radicals, R^\cdot , in growing PSt and PMMA chains. Finally, in practice, the use of a high polymerization temperature is beneficial, particularly for Cl ATRP (Table 5). In fact, many ATRA processes also appear to use rather high temperatures.

Prior to the present invention, $RuCl_2(PPh_3)_3$ was known to promote only the monomeric addition of CCl_4 to alkenes. Very recently, it was reported that $RuCl_2(PPh_3)_3$ induced the controlled radical polymerization of MMA at $60^\circ C$ in the presence of methylaluminum bis(2,4-di-tert-butylphenoxide) (Sawamoto et al, *Macromolecules*, 1995, 28, 1721). However, the present inventors observed that at high polymerization temperatures (e.g., $130^\circ C$, a number of radically polymerizable monomers undergo ATRP in the absence of methylaluminum bis(2,4-di-tert-butylphenoxide) or other such activators. As a result, one may increase polymerization temperature (rather than include methylaluminum bis(2,4-di-tert-butylphenoxide) or

other activator) as a means to enhance the reactivity of less reactive monomeric or polymeric halides towards transition metal species with the formation of propagation radicals. Indeed, it is possible that an activator may lead to a change in the polymerization mechanism.

Radical Addition vs Coordination Insertion. Regarding the mechanism of ATRP, the important question to be answered is whether the ATRP really involves radical intermediates during polymerization.

The generation of radical intermediates by reacting some transition metal species, including salts and/or complexes of copper, ruthenium, iron, vanadium, niobium, and others, with alkyl halides, R-X, is well documented (see (a) Bellus, D. *Pure & Appl. Chem.* **1985**, 57, 1827; (b) Nagashima, H.; Ozaki, N.; Ishii, M.; Seki, K.; Washiyama, M.; Itoh, K. *J. Org. Chem.* **1993**, 58, 464; (c) Udding, J. H.; Tuijp, K. J. M.; van Zanden, M. N. A.; Hiemstra, H.; Speckamp, W. N. *J. Org. Chem.* **1994**, 59, 1993; (c) Seijas et al, *Tetrahedron*, **1992**, 48(9), 1637; (d) Nagashima, H.; Wakamatsu, H.; Ozaki, N.; Ishii, T.; Watanabe, M.; Tajima, T.; Itoh, K. *J. Org. Chem.* **1992**, 57, 1682; (e) Hayes, T. K.; Villani, R.; Weinreb, S. M. *J. Am. Chem. Soc.* **1988**, 110, 5533; (f) Hirao et al, *Syn. Lett.*, **1990**, 217; and (g) Hirao et al, *J. Synth. Org. Chem. (Japan)*, **1994**, 52(3), 197; (h) Iqbal, J.; Bhatia, B.; Nayyar, N. K. *Chem. Rev.*, **94**, 519 (1994); and Kochi, J.K., *Organometallic*

Mechanisms and Catalysis, Academic Press, New York, 1978, and references cited therein). Moreover, it is also known that R-X/transition metal species-based redox initiators, such as $\text{Mo}(\text{CO})_6/\text{CHCl}_3$, $\text{Cr}(\text{CO})_5/\text{CCl}_4$, $\text{Co}_4(\text{CO})_{12}/\text{CCl}_4$, and $\text{Ni}[\text{P}(\text{OPh})_3]_4/\text{CCl}_4$, promote radical polymerization (see Bamford, *Comprehensive Polymer Science*, Allen, G., Aggarwal, S. L., Russo, S., eds., Pergamon: Oxford, 1991, vol. 3, p. 123). The participation of free radicals in these redox initiator-promoted polymerizations was supported by end-group analysis and direct observation of radicals by ESR spectroscopy (see Bamford, *Proc. Roy. Soc.*, 1972, A, 326, 431).

However, different transition metal species may act in a different manner. They may induce an atom transfer reaction or provide a source of metal-complexed radicals or even initiate a catalytic cycle that does not involve radical intermediates (Curran et al, *J. Org. Chem.* and *J. Am. Chem. Soc.*, *supra*).

In fact, several examples using additives such as CuX , a catalyst suitable for the present invention, reported previously showed that the reactions between some polyhaloalkanes, e.g., CCl_4 , and alkenes exceptionally lead to exclusive 1:1 adducts in many cases (Bellus, *supra*). The authors argued that, if radical addition were the case, a considerable amount of telomer formation would be expected even at high organic polyhalide/alkene ratios. Thus, they questioned whether Cu(I)Cl cleaves the carbon-halogen bond by

an atom transfer process to generate a carbon radical and a Cu(II) species (Fig. 2) or by an overall two-electron change to generate a Cu(III) species 2 (Fig. 15), followed by insertion of the alkene into the carbon-copper(III) σ -bond and halogen ligand transfer (reductive elimination) with a new Cu(III) species 3 formed.

In sharp contrast to previous observations, the present invention shows that the polymerization of alkenes occurs when halide initiators, including CCl_4 , are used with CuX complexed by Bpy as a catalyst. The uncomplexed CuX species may not be powerful enough to abstract the halogen atom from the 1:1 monomeric adduct to promote atom transfer radical polymerization. As described below, the polymerization of St initiated with 1-PECl/CuCl without ligand is an ill-controlled, thermally self-initiated polymerization.


Moreover, the similarities in stereochemistry of the polymerizations of MMA initiated with classic radical initiators and various initiator/CuX/Bpy systems (Table 2) suggests that a putative insertion process (Fig. 16) can be rejected. Although metal coordinated radicals (Fig. 17) may be involved in the polymerizations of alkenes initiated with the R-X/CuX/Bpy system, a simple radical process is most probable (Fig. 2). The participation of the free radical intermediates is also supported by the observation that addition of 1.5 molar equiv. of galvinoxyl (relative to 1-PECl) effectively inhibits polymerization, and no styrene

polymerization was initiated with 1-PECl/CuCl/Bpy (1/1/3) within 18 hours. Further evidence for the presence of radical intermediated in ATRP is the fact that the monomer reactivity ratios for ATRP random copolymerization resembles the monomer reactivity ratios for classical radical polymerization processes (i.e., $r_{MMA} = 0.46/r_{St} = 0.48$ for ATRP at 100°C initiated with 2-EiBBr/CuBr/Bpy, and $r_{MMA} = 0.46/r_{St} = 0.52$ for radical polymerization initiated with BPO at 60°C).


Atom Transfer Radical Polymerization vs. Redox Radical Telomerization. It is well known that radical telomerization can be initiated by a transition metal species-based redox catalyst. The mechanism is generally described as shown below:

Scheme 2

Initiation:




Propagation:



Chain Transfer:



Termination:



5 The fundamental differences between ATRP and redox radical telomerization are as follows. In ATRP, the polymeric halides, $\text{R-M}_n\text{-X}$, behave as *dormant* species (Fig. 2). They can be repeatedly activated by transition metal species, M_t^n , to form the growing radicals, R-M_n^{\cdot} , and oxidized transition metal species, M_t^{n+1} , which can further react with R-M_n^{\cdot} to regenerate $\text{R-M}_n\text{-X}$ and M_t^n , i.e., a *reversible* transfer process.

10 Contrary to ATRP, redox radical telomerization represents a *degradative* transfer process, in which the resulting polymeric halides, $\text{R-M}_n\text{-X}$, are *dead* chains (see Scheme 2 above). Consequently, the molecular weight obtained in redox radical telomerization does not increase with the monomer conversion, whereas the molecular weight increases linearly with increasing monomer conversion in ATRP.

Factors Affecting Atom Transfer Radical Polymerization.

20 (a) "Living"/Controlled Radical Polymerization. To better describe controlled ATRP, a discussion of some general properties for "living"/controlled radical polymerization is in order.

Free radicals, which are the growing species in radical polymerization, are highly reactive species. Unlike anions or cations, they recombine and/or disproportionate at rates


05034187 030398

approaching the diffusion controlled limit (i.e., k_t of about $10^8-10^{10} \text{ M}^{-1} \cdot \text{sec}^{-1}$), which is much higher than the corresponding propagating rate constant (i.e., $k_p \sim 10^{2-4} \text{ M}^{-1} \cdot \text{sec}^{-1}$).

Moreover, initiation is incomplete due to slow decomposition of classic radical initiator (i.e., $k_d \sim 10^{-4-6} \text{ sec}^{-1}$). These are the kinetic reasons why classic radical polymerization yields ill-defined polymers with unpredictable molecular weight, broad molecular weight distribution, and uncontrolled structures.

Moreover, due to the same kinetic reasons, it is impossible to entirely suppress the termination reactions and to obtain a *living* radical polymerization, in which chain breaking (termination) reactions are absent (Szwarc, *Nature*, 1956, 176, 1168). Thus, for the sake of the accuracy, we propose the term *controlled* or "*living*" radical polymerization to describe the processes in which the side reactions are not significant. Consequently, structural parameters, such as molecular dimension, molecular weight distribution, composition, topology, functionality, etc., can be controlled to some extent.

The preparation of controlled polymers in a "living" radical process requires a low stationary concentration of growing radicals, M_n^{\cdot} , which are in a fast dynamic equilibrium with the dormant species, M_n-D :



Termination is second order and propagation is first order in respect to growing radicals (eqs. (12) and (13):

$$R_p = d(\ln[M])/dt = k_p[M] \times [P\cdot] \quad (12)$$

$$R_t = -d[P\cdot]/dt = k_t \times [P\cdot]^2 \quad (13)$$

At low concentration of free radicals, the proportion of termination versus propagation is reduced. If the reversible exchange between growing radicals, $M_n\cdot$, and dormant species, M_n-D , is fast, the polymerization degree can be predetermined by the ratio of the concentration of the consumed monomer to that of the dormant chains (eq. 14), and the molecular weight distribution may remain narrow.

$$DP_n = \Delta[M]/[M_n-D] = \Delta[M]/[I]_0 \quad (14)$$

Recent progress in controlled radical polymerization can be indeed related to the approach illustrated in the M_n-D reaction above, in which growing radicals, $M_n\cdot$, react reversibly with species D, which may be carbon-, sulfur-, and oxygen-centered radicals (Otsu et al, *Makromol. Chem, Rapid Commun.*, **1982**, 127; Otsu et al, *Macromolecules*, **1992**, 25, 5554; Bledzki et al, *Makromol. Chem*, **1983**, 184, 745; Druliner, *Macromolecules*, **1991**, 24, 6079; U.S. Patent No. 4,581,429; and Georges et al, *Macromolecules*, **1993**, 26, 2987), alkylaluminum complexes (Mardare et al, *Macromolecules*, **1994**, 27, 645), and

organocobalt porphyrin complexes (Wayland, B. B., Pszmik, G., Mukerjee, S. L., Fryd, M. J. *Am. Chem. Soc.*, **1994**, 116, 7943), in a reversible deactivated process. Another approach (discovered by the present inventors) is based on using alkyl iodides in a degenerative transfer.

The Significance of the Presence of the Low Concentration of Growing Radicals in Maintaining "Living" ATRP. Since ATRP promoted by the Cu(I)/Cu(II) redox process resembles classic radical polymerization, termination reactions can not completely eliminated, which are second order in respect to growing radicals (eq. 13). As already discussed in the preceding section, if the concentration of growing radicals is kept low enough, and a fast and reversible equilibrium between growing radicals and dormant species is established (see Scheme 2 above), the proportion of termination in comparison to propagation can be minimized, resulting in a predictable molecular weight and a narrow molecular weight distribution. Indeed, this is the case for "living" ATRP.

Table 6 lists the estimated polymerization time for 90% monomer conversion, $t_{0.9}$, concentration of the dead polymer chains due to the spontaneous termination reactions at that time, $[P]_{d,0.9}$, concentration of the polymer chains due to self-initiation, $[P]_{self,0.9}$, and percentage of uncontrolled polymer chains generated by side reactions, "UC", in bulk ATRP of St, MMA, and MA initiated with 1-PECl/CuCl/Bpy at 130°C:

$$\ln ([M]_0/[M]) = \ln (10) = k_p^{app} \times t_{0.9} \quad (15)$$

$$[P]_{t,0.9} = R_t \times t_{0.9} \quad (16)$$

$$[P]_{self,0.9} = R_{i,self} \times t_{0.9} \quad (17)$$

$$"UC" = ([P]_{self,0.9} + [P]_{d,0.9}) / \{[R-X]_0 + [P]_{self,0.9} + [P]_{d,0.9}\} \quad (18)$$

Table 6

Estimated $[P]$, $t_{0.9}$, $[P]_{self,0.9}$, $[P]_{d,0.9}$, and "UC"
for Bulk ATRP of St, MMA and MA Initiated with
1-PECl/CuCl/Bpy (1/1/3) at 130°C

Monomer	MA	MMA	St
$[1-PECl]_0$ (mol/l)	0.038	0.038	0.038
$[M]_0$ (mol/l)	11.1	9.36	8.7
$k_{p,130^\circ C}$ (M s ⁻¹) ^a	14,100	3170	6870
$k_{t,130^\circ C}$ (10 ⁷ s ⁻¹) ^b	1.98	0.31	0.532
$k_p^{app,130^\circ C}$ (10 ⁻⁴ s ⁻¹)	3.14	5.83	1.35
$[P]$ (10 ⁻⁷ M) ^a	0.22	1.84	0.19
$t_{0.90}$ (s ⁻¹)	7300	4000	17100
$[P]_{d,0.90}$ (10 ⁻⁴ mol/l)	0.7	4.20	1.22
$[P]_{self,0.90}$ (10 ⁻³ mol/l)	--	--	1.7
"UC", %	0.2	1.1	4.5

^a: see Table 4; ^b: Data from Odian, G. *Principles of Polymerization*, Wiley-Interscience, John Wiley & Sons, New York, 1991; $\ln k_{t,MA} = 23.43 - (2671/T)$, $\ln k_{t,MMA} = 18.5 - (1432/T)$, $\ln k_{t,St} = 17.47 - (962/T)$.

As shown in Table 6, at 90% monomer conversion, the concentrations of uncontrolled polymer chains, "UC", are all less than 3% in ATRP's of St, MMA, and MA, when 1-PECl/CuCl/Bpy (1/1/3) is used as the initiator system at 130°C. This may be why ATRP proceeds in a "living" manner. Although the termination rate constant is larger in MA radical polymerization than in the other two processes, ATRP of MA is better controlled than ATRPs of St and MMA. This appears to be due to a lower concentration of growing radicals in the ATRP of MA (Table 6).

The Significance of the Presence of Fast Exchange Between $R-M_n-X$ and $R-M_n\cdot$ in Inducing Low Polydispersity in ATRP. At a low concentration of radicals (Tables 4-6), ca. 10^{-7} to about 10^{-8} mol/l, polymers with very high and uncontrolled molecular weights are usually found. To cope with this problem, a reversible equilibrium between a minute amount of growing, radicals and a large amount of the dormant species needs to be established. Moreover, only if both (1) the initiation reaction between initiating radicals and monomer and (2) the exchange reaction between the growing radicals and the dormant species are faster than (3) the propagation reaction between the growing radicals and the monomer, the molecular weight of the resulting polymers can be predicted by eq. (14), and low polydispersity polymers can be obtained.

Moreover, in a so-called "living" system with reversible dynamic exchange, there is evidence that the polydispersity of the resulting polymers largely depends on the ratio of the deactivation rate to the propagation rate (Matyjaszewski, K. Polym. Prep. (Am. Chem. Soc. Polym. Chem. Div.), 1995, 36(1), 541). On the other hand, it has been demonstrated that many transition metal species can be used as efficient retarders or inhibitors in radical polymerization (Bamford, Comprehensive Polymer Science, Allen, G., Aggarwal, S. L., Russo, S., eds., Pergamon: Oxford, 1991, p. 1). For example, the reaction rate constants between (1) PSt[•] and CuCl₂ and (2) PMMA[•] radicals and CuCl₂ are 10⁴ and 10³ times greater in comparison with the corresponding propagation rate constants, respectively.

Therefore, the existence of a fast deactivation (scavenging) reaction can explain the low polydispersity obtained in ATRP.

Earlier, Otsu et al reported that an R-Cl/Ni(0) combined initiator system can induce a "living" radical polymerization of St and MMA at 60°C (Chem. Express, 1990, 5(10), 801).


However, the "living" character of the R-Cl/Ni(0) combined initiator of Otsu et al may not be entirely accurate, since (1) the molecular weight of the obtained polymers did not increase linearly with respect to monomer conversion, (2) the initiator efficiency is low (about 1% based on R-Cl), and (3) the molecular weight distribution is broad and bimodal. The same phenomena were also observed by the present inventors.

Thus, it appears that the R-Cl/Ni(0) combined initiator of Otsu et al does not provide controlled polymers.

Based on the published evidence, the R-Cl/Ni(0) combined initiator of Otsu et al appears to act as a conventional redox initiator, similar to the initiators developed by Bamford (see *Reactivity, Mechanism and Structure in Polymer Chemistry*, Jenkins, A. D. and Ledwith, A., eds, John Wiley & Sons, London (1974), p. 52; and *Comprehensive Polymer Science*, Allen, G., Aggarwal, S. L., Russo, S., eds., Pergamon: Oxford, 1991, vol. 3, p. 123). The very low initiator efficiency and a broad, bimodal molecular weight distribution observed in the system of Otsu et al suggests that in that system, the small amount of initiating radicals were generated by a redox reaction between R-Cl and Ni(0), and the reversible deactivation of initiating radicals by oxidized Ni species is inefficient in comparison to propagation. This may support the idea that fast exchange between R-X and R \cdot in transition metal-promoted ATRP at the initial step is one of the key factors controlling initiator efficiency and molecular weight distribution.

The Factors Affecting the Concentrations of the Growing Radicals and the Exchange Rate Between R-M $_n$ -X and R-M $_n$ \cdot in ATRP. Based on the results shown herein, the factors affecting the concentrations of the growing (initiating) radicals and the exchange rate between R-M $_n$ -X (R-X) and R-M $_n$ \cdot (R \cdot) in ATRP can be qualitatively discussed.

The stationary concentration of growing radicals can be expressed as in eq. (20):



$$K = k_{\text{act.}}/k_{\text{deact.}} = ([\text{M}_n^{\cdot}] \times [\text{CuX}_2])/([\text{Mn-X}] \times [\text{CuX}]) \approx [\text{M}_n^{\cdot}]^2/([\text{R-X}]_0 \times [\text{CuX}]_0) \quad (19)$$

$$[\text{M}_n^{\cdot}] = \{(k_{\text{act.}}/k_{\text{deact.}}) \times ([\text{R-X}]_0 \times [\text{CuX}]_0)\}^{1/2} \quad (20)$$

An increase in $[\text{R-X}]_0$ and $[\text{CuX}]_0$ results in an increase in the concentration of growing radicals, and subsequently, in the polymerization rate (Figure 12).

As also seen from eq. (20), the concentration of growing (initiating) radicals is proportional and inversely proportional to the activation and deactivation rate constants, respectively, which strongly depend on the structure of the $\text{R}^{11}\text{R}^{12}\text{R}^{13}\text{C}$ group in the initiator, the structure of the repeating monomer units M in $\text{R-M}_n\text{-X}$, the leaving group X, and the polymerization temperature (see Tables 3, 4 and 5, Figure 9).

In terms of polarity, the deactivation reaction between PMA^{\cdot} and CuCl_2 is usually 10 times slower than that between Pst^{\cdot} and CuCl_2 (i.e., $k_{\text{deact. Pst}^{\cdot}/\text{CuCl}_2} > k_{\text{deact. PMA}^{\cdot}/\text{CuCl}_2}$) (see Bamford, *Comprehensive Polymer Science*, Allen, G., Aggarwal, S. L., Russo, S., eds., Pergamon: Oxford, 1991, p. 1). Thus, the similar concentration of radicals found in the ATRP of St

relative to the ATRP of MA indicates that the activation reaction between CuCl and PSt-Cl is faster than the one between PMA-Cl and CuCl (i.e., $k_{\text{act. PSt-Cl}} > k_{\text{act. PMA-Cl}}$). This is in good agreement with the lower bond dissociation energy in PSt-Cl as compared to PMA-Cl (see Danen, W. C., in *Methods in Free Radical Chemistry*, Huyser, E. L. S., ed., Dekker, New York, 1974, vol. 5, p.1; and Poutsma, *supra*). The higher concentration of growing radicals found in the ATRP of MMA as compared to the ATRP's of St and MA (see Table 4) implies that steric hindrance in both the polymeric halide PMMA-Cl and growing radical PMMA \cdot may significantly affect deactivation and activation rates.

As noted in Figures 10 and 11, the polymerization is much faster in the Br-ATRP of MA than in the Cl-ATRP of MA, due to a higher stationary concentration of radicals in the former system as compared to the latter one. However, the polydispersity is much narrower in Br ATRP than in Cl-ATRP. According to the discussion in the preceding section, this suggests that deactivation of free radicals with CuBr₂ is faster in comparison to deactivation of free radicals with CuCl₂. Since the concentration of growing radicals in Br-ATRP is larger than in Cl-ATRP (see Table 5), the activation of PMA-Br by Br-containing Cu(I) species must be faster than the activation of PMA-Cl by Cl-containing Cu(I) species. This is also in accordance with the fact that the ease of the abstraction of X from R-X by CuX follows the order Br > Cl

(i.e., the lower the bond dissociation energy in R-X, the easier to abstract an X atom; see Curran, *Synthesis*, in *Free Radicals in Synthesis and Biology*, and in *Comprehensive Organic Synthesis*; Danen; and Poutsma, all *supra*).

5 **Halogen Atom Transfer (Abstraction) vs. Outer-Sphere Electron Transfer.** The generation of free radicals by reacting an organic halide with a transition metal compound may involve two different mechanisms: either halogen atom transfer (Figure 18A) or outer-sphere electron transfer (Figure 18B). The former process depends on the carbon-halogen bond dissociation energy, whereas the latter is a function of the electrode potential for the reaction of the organic halide (i.e., $RX + e^- \rightarrow R^\cdot + X^-$).

10
15 The outer sphere electron transfer process is usually less sensitive than halogen atom transfer to the leaving atom X in R-X and to temperature (Howes et al, *Inorg. Chem.* **1988**, 27, 3147; and references therein). As discussed before, the results presented herein show that transition metal mediated ATRP has a strong dependence on the leaving group X in R-X, as well as on the reaction temperature. Thus, the results herein suggest that ATRP involves a direct atom transfer process.

20
25 Alternatively, the reversible conversion of the radicals R^\cdot and $R-M_n^\cdot$ to organic halides R-X and $R-M_n-X$ may involve direct atom transfer (see Kochi, J.K., *Organometallic Mechanisms and Catalysis*, Academic Press, New York, 1978, and

references cited therein; Asscher, M., Vofsi, D. *J. Chem. Soc., Perkin II.* 1968, 947; and Cohen, H., Meyerstein, D. *Inorg. Chem.* 1974, 13, 2434) or oxidative addition/reductive elimination with the formation of organocopper(III)

5 intermediates (see Kochi, *supra*; Orochov, A., Asscher, M., Vofsi D. *J. Chem. Soc., Perkin II.* 1973, 1000; and Mitani, M., Kato, L., Koyama, K. *J. Am. Chem. Soc.* 1983, 105, 6719). Generally, it is difficult to distinguish between these two mechanisms. Nevertheless, the organocopper(III) species, if
10 they exist, probably do not react directly with monomer. Otherwise, some effect on tacticity would be observed.

Thus a successful extension of atom transfer radical addition, ATRA, to atom transfer radical polymerization, ATRP
15 has been demonstrated in a Cu(I)/Cu(II) model redox process. The present process opens a new pathway to conduct a "living" or controlled radical polymerization of alkenes. The controlled process found in ATRP results from two important contributions: (1) a low stationary concentration of growing radicals and (2) a fast and reversible equilibrium between the
20 growing radicals and the dormant species. Many parameters, such as the nature of transition metals, the structure and property of ligands, the polymerization conditions, etc, may affect the course of "living" ATRP. On the other hand, it is anticipated that, like other controlled polymerizations, ATRP
25 will provide a powerful tool for producing various tailor-made polymers.

RECEIVED "CATHEDRO"

Other features of the present invention will become apparent in the course of the following descriptions of exemplary embodiments which are given for illustration of the invention, and are not intended to be limiting thereof.

EXAMPLES

Example 1:

An aralkyl chloride, 1-phenylethyl chloride, 1-PECl, is an efficient initiator, and a transition metal halide, CuCl, complexed by 2,2'-bipyridine, bpy, is an efficient chlorine atom transfer promoter. This model initiating system affords controlled polymers with predicted molecular weight and narrower molecular weight distribution, $M_w/M_n < 1.5$, than obtained by conventional free radical polymerization.

Phenylethyl chloride, 1-PECl, was prepared according to a literature procedure (Landini, D.; Rolla, F. *J. Org. Chem.*, **1980**, 45, 3527).

A typical polymerization was carried out by heating a reddish brown solution of styrene (St), 1-PECl (0.01 molar equiv. relative to monomer), CuCl (1 molar equiv. relative to 1-PECl), and bpy (3 molar equiv. relative to CuCl), in a glass tube sealed under vacuum at 130°C. (The reddish brown color of a slightly heterogeneous solution was formed within 30 seconds at 130°C.) The formed polymer was then dissolved in THF and precipitated in MeOH (three times), filtered and dried at 60°C under vacuum for 48 hr. Yield, 95%. A linear

increase in the number average molecular weight, $M_{n,SEC}$, versus monomer conversions up to 95% was found for PMA. $M_{n,SEC}$ values were determined by size exclusive chromatography, and were calibrated using polystyrene standards.

5 The $M_{n,SEC}$ is very close to the theoretical one, $M_{n,th}$, calculated by the following equation (21):

$$M_{n,th} = ([M]_0/[1-PECl]_0) \times (MW)_0 \times \text{conversion} \quad (21)$$

10 [M]₀ and [1-PECl]₀ represent the initial concentrations of monomer (St) and 1-PECl, respectively, and (MW)₀ is the molecular weight of monomer. These results indicate that 1-PECl acts as an efficient initiator, and that the number of the chains is constant. The molecular weight distribution is fairly narrow ($M_w/M_n = 1.3-1.45$). The linear plot of $\ln([M]_0/[M])$ versus polymerization time (e.g., Figure 3)

15 implies that the concentration of growing radicals remains constant during propagation, and that termination is not significant. Both of these results suggest a "living" polymerization process with a negligible amount of transfer and termination.

20 Additionally, a series of experiments has been carried out at 130°C, using various $[M]_0/[1-PECl]_0$ ratios and a constant $[1-PECl]_0/[CuCl]_0/[bpy]_0$ ratio of 1:1:3. Similar to Figure 5, a graph was prepared which compares the $M_{n,SEC}$ and calculated $M_{n,th}$, based on equation (21) above.

A linear plot is observed in the molecular weight range from 3.8×10^3 to 1.05×10^5 g/mol. The slope of the straight line is 0.93, indicating a high initiator efficiency. The polydispersities of all the polymers obtained also remain low and are smaller than in a conventional radical polymerization i.e., $M_w/M_n < 1.5$. These results again support a "living" polymerization process initiated with 1-PECl/CuCl/Bpy system.

Table 7 summarizes the results of styrene polymerization under various experimental conditions. In the absence of 1-PECl, CuCl or bpy, the polymers obtained are ill-controlled with unpredictable molecular weights and with broad molecular weight distributions.

09034187-030393

Table 7

Results of Styrene Bulk Polymerization at 130°C

[St] ₀ (mmol)	Conv. (%)	[1-PECl] ₀ (mmol)	[CuCl] ₀ (mmol)	[byp] ₀ (mmol)	M _{n,th.} ^a	M _{n,SEC}	M _w /M _n
4.375	15	0	0	0	0	132,100	1.76
4.375	52	0	0.182	0.54	0	134,700	1.95
4.375	40	0.0528	0.0455	0	3,400	68,700	3.10
4.40	45	0.0528	0	0.135	4,100	76,500	2.10

^a calculated based on eq. 21

Example 2:

The same initiating system, 1-PECl/CuCl/Bpy (1/1/3), can be also used for the controlled polymerization of acrylic monomers, such as methyl methacrylate, MMA, methyl acrylate, MA, and butyl acrylate, BA. Block copolymers of St and MA have been produced using the same technique as described in Example 1 for homopolymerization of styrene (see the Examples below). Heating of chlorine atom end-capped polystyrene (0.5 g, $M_n = 4000$, $M_w/M_n = 1.45$) and a two-fold excess of MA (1.0 g) in the presence of 1 molar equiv. of CuCl and 3 molar equiv. of bpy (both relative to polystyrene) at 130°C results in MA block polymerization to form the desired PSt-b-PMA block copolymer (yield: 95%, $M_n = 13,000$, $M_w/M_n = 1.35$).

Discussion

By analogy with transition metal catalyzed atom transfer radical addition reactions (ATRA), used in organic synthesis, the results presented herein can be explained by the mechanism shown in Fig. 2. The present process appears to involve a succession of ATRA processes, and therefore, can be called atom transfer radical polymerization, ATRP.

The model catalyst Cu^ICl acts as a carrier of the chlorine atom in a redox reaction between Cu(I) and Cu(II). The coordination of the bidentate nitrogen ligand to Cu^ICl increases the solubility of the inorganic salt and can also affect the position of the redox equilibrium, so as to

facilitate the abstraction of a chlorine from the initiator, 1-PECl, and the dormant species, $P_i\text{-Cl}$, with the formation of initiating and growing radicals, respectively. The reversible conversion of radicals, R^\cdot and P_i^\cdot , to the corresponding halides, $R\text{-Cl}$ and $P_i\text{-Cl}$, may involve a direct atom transfer reaction (Kochi, J.K. *Organometallic Mechanisms and Catalysis*, Academic Press: New York, 1978, and references therein; Asscher, M., Vofsi, D. *J. Chem. Soc., Perkin II*. 1968, 947; Cohen, H., Meyerstein, D. *Inorg. Chem.* 1974, 13, 2434) or oxidative addition/reductive elimination with the formation of the organocopper (III) intermediates (Kochi, supra; Orochov, A., Asscher, M., Vofsi D. *J. Chem. Soc., Perkin II*. 1973, 1000; Mitani, M., Kato, L., Koyama, K. *J. Am. Chem. Soc.* 1983, 105, 6719). If the concentration of growing radicals is low and the redox reaction is fast compared to bimolecular reactions of the radicals, the extent of the termination reactions is minimized, resulting in a "living" process. Moreover, if the rate of reversible exchange between $P_i\text{-Cl}$ and P_i^\cdot is comparable to that of propagation, the number average molecular weight should be defined by eq. (21), and the molecular weight distribution should remain narrow.

Two observations support the participation of free radicals in ATRP. First, the tacticity of the polymers is similar to those synthesized by typical radical initiators. For example, the tacticity of poly(methyl methacrylate) $M_n =$

35,400, $M_w/M_n = 1.40$) synthesized using a 1-PECl/CuCl/Bpy initiator system (in a 1:1:3 molar ratio) at 130°C is $rr/mr(rm)/mm$: 53/38/9. These values are very close to those of PMMA prepared using a typical radical initiator, BPO, at the same temperature. Therefore, the organocuprate(III) species, if it exists, probably does not react directly with monomer, otherwise some effect on tacticity would be expected. Secondly, addition of 1.5 molar equiv. of galvinoxyl (relative to 1-PECl) effectively inhibits the polymerization. In the presence of galvinoxyl, no styrene polymerization was found within 18 hours.

The low proportion of termination, despite the relatively rapid polymerization, may be explained by stabilizing interactions between radicals P_i^\cdot and $CuCl_2$. It may be possible that the monomer reacts with a radical P_i^\cdot within a solvent cage, in which the ratio of rate constants of propagation to termination is higher than for uncomplexed radicals in solution.

At 130°C, styrene may polymerize thermally by self-initiation. (Moad, G., Rizzardo, E., Solomon, D. H. *Polym. Bull.*, 1982, 6, 589). The contribution of this reaction in ATRP is rather small, because (1) ATRP is fast and (2) the relative rate of self-initiation is further reduced with the progress of the reaction. However, the small contribution of self-initiation may enhance polydispersities to the range of

$M_w/M_n \approx 1.4$, and may reduce molecular weights to slightly lower values than theoretically predicted.

It must be stressed that the present transition-metal promoted ATRP, in which the molecular weight linearly increases with monomer conversion, is very different from typical redox radical telomerization promoted by transition metal species in which the molecular weight does not increase with conversion (Boutevin, B., Pietrasant, Y., in *Comprehensive Polymer Science*, Allen, G., Aggarwal, S. L., Russo, S., eds., Pergamon: Oxford, 1991, vol. 3. p 185; Bamford, C. H., in *Comprehensive Polymer Science (First Supplement)*, Allen, G., Aggarwal, S. L., Russo, S., eds., Pergamon: Oxford, 1991, p. 1).

In conclusion, the model alkyl chloride initiator, 1-PECl, and model transition metal complex CuCl/bpy polymerize styrene by repetitive atom transfer radical additions to give well-defined high molecular weight polymers with narrow molecular weight distributions.

For examples 3-22, the polymers were isolated by either of two procedures:

- (1) The polymer was dissolved in THF and precipitated in MeOH (three times), filtered and dried under vacuum; or
- (2) The heterogeneous reaction solution was filtered, and the solvent was removed under vacuum.

Removal of solvent or drying can optionally be conducted using mild heat (e.g., 25-60°C). The same polymeric product is obtained, regardless of the isolation procedure.

Monomers, and ethyl acetate were vacuum-distilled over CaH_2 before use. CuCl and CuBr were purified according to the known procedures (see Nagashima, H.; Ozaki, N.; Ishii, M.; Seki, K.; Washiyama, M.; Itoh, K. *J. Org. Chem.* **1993**, *58*, 464; (c) Udding, J. H.; Tuijp, K. J. M.; van Zanden, M. N. A.; Hiemstra, H.; Speckamp, W. N. *J. Org. Chem.* **1994**, *59*, 1993; (c) Seijas et al, *Tetrahedron*, **1992**, *48*(9), 1637; (d) Nagashima, H.; Wakamatsu, H.; Ozaki, N.; Ishii, T.; Watanabe, M.; Tajima, T.; Itoh, K. *J. Org. Chem.* **1992**, *57*, 1682).

Example 3:

Polystyrene was prepared by heating styrene (0.9 g), 1-phenylethyl chloride (1 μL , 7.54×10^{-6} mol), Cu(I)Cl (7.54×10^{-6} mol) and 2,2'-bipyridine (Bpy; 2.26×10^{-5} mol) at 130° in a sealed tube for 21.5 h. The polymerization reaction mixture was then dissolved in THF, and precipitated in methanol. The precipitated polymer was filtered, and the dissolving, precipitating and filtering steps were repeated two additional times. The obtained polymer was dried at 60°C under vacuum for 48 h.

The dried polymer had a number average molecular weight as measured by size exclusion chromatography (SEC), M_{nSEC} , of 95,000, in good agreement with the theoretical number average

molecular weight, $M_{n,th.}$, of 102,000. The dried polymer was obtained in 85% yield. The polydispersity, M_w/M_n , was 1.45.

Example 4:

Polystyrene was prepared according to the procedure described in Example 3, except polymerization was conducted at 100°C for 88 h. The polymer was obtained in 80% yield. The $M_{n,SEC}$ of 93,300 was in excellent agreement with the $M_{n,th.}$ of 97,000. The M_w/M_n of the obtained polymer was 1.50.

Example 5:

The procedure of Example 3 was repeated, except that 0.45 g of styrene and 2.5 μ L (1.89×10^{-5} mol) of 1-PECl were employed, Ni(0) (2.73×10^{-5} mol) was used as the transition metal in place of Cu(I)Cl, and PPh_3 (1.41×10^{-4} mol) was used as the ligand in place of Bpy. The reaction was conducted at 130°C for 12 h.

The polymer was obtained in 85% yield. The $M_{n,SEC}$ of the obtained polymer was 189,000 ($M_{n,th.} = 17,000$), and the $M_w/M_n = 1.70$.

Example 6:

Polystyrene was prepared according to the procedure of Example 3, except that the concentration of 1-PECl was 2.26×10^{-5} mol (amount = 3 μ L), $RuCl_2$ (2.26×10^{-5} mol) was used in place of Cu(I)Cl, and PPh_3 (6.78×10^{-5} mol) was used in place

of Bpy. The polymerization was conducted at 130°C for 13.5 h. The polymer was obtained in 90% yield. The $M_{n,SEC}$ of 18,300 was in excellent agreement with the $M_{n,th.}$ of 17,900. The obtained polymer had an M_w/M_n of 2.0.

5 Example 7:

6
7
8
9
10 Polystyrene was prepared according to the procedure of Example 3, except that AIBN (1.7×10^{-5} mol) was used in place of 1-PECl, Cu(II)Cl₂ (3×10^{-5} mol) was used in place of Cu(I)Cl, and Bpy was present in a molar amount of 7×10^{-5} mol. The polymerization was conducted at 130°C for 5 h. The polymer was obtained in 90% yield. The $M_{n,SEC}$ of 18,500 was in agreement with the $M_{n,th.}$ of 25,000. The obtained polymer had an M_w/M_n of 1.7.

15 Example 8:

16
17
18
19
20 Polystyrene was prepared according to the procedure of Example 3, except that 2-chloropropionitrile (3.75×10^{-6} mol) was used in place of 1-PECl; Cu(I)Cl and Cu(II)Cl₂ were used in an equimolar mixture (3.76×10^{-6} mol of each) in place of Cu(I)Cl alone; and Bpy was present in a molar amount of 1.9×10^{-5} mol. The polymerization was conducted at 130°C for 33 h. The polymer was obtained in 80% yield. The $M_{n,SEC}$ of 81,500 was in good agreement with the $M_{n,th.}$ of 95,500. The obtained polymer had an M_w/M_n of 1.4.

RECEIVED " 28TH 1960

Example 9:

Polystyrene was prepared according to the procedure of Example 3, except that benzyl chloride (3.75×10^{-5} mol) was used in place of 1-PECl, FeCl_2 (3.75×10^{-5} mol) was used in place of Cu(I)Cl , and $(\text{EtO})_3\text{P}$ (1.15×10^{-4} mol) was used in place of Bpy. The polymerization was conducted at 130°C for 5.5 h. The polymer was obtained in 85% yield. The $M_{n,\text{SEC}}$ of 19,300 was in good agreement with the $M_{n,\text{th}}$ of 21,100. The obtained polymer had an M_w/M_n of 3.0.

Example 10:

Poly(methyl acrylate), PMA, was prepared according to the procedure of Example 3, except that 1.45 grams of MA were used, α,α' -dibromoxylene (4.4×10^{-5} mol) was used in place of 1-PECl, Cu(I)Br (8×10^{-5} mol) was used in place of Cu(I)Cl , and Bpy was present in a molar amount of 2.5×10^{-4} mol. The polymerization was conducted at 80°C for 36 h. The polymer was obtained in 90% yield. The $M_{n,\text{SEC}}$ of 31,000 was in very good agreement with the $M_{n,\text{th}}$ of 29,500. The obtained polymer had an M_w/M_n of 1.2.

Example 11:

Poly(methyl acrylate) was prepared according to the procedure of Example 10, except that 0.48 g of MA were used, 2-methylbromopropionate (1.47×10^{-5} mol) was used in place of α,α' -dibromoxylene, Cu(I)Br was used in an amount of $1.47 \times$

10⁻⁵ mol, and Bpy was present in a molar amount of 4.5 x 10⁻⁵ mol. The polymerization was conducted at 100°C for 15 h. The polymer was obtained in 95% yield. The $M_{n,SEC}$ of 29,500 was in very good agreement with the $M_{n,th.}$ of 31,000. The obtained polymer had an M_w/M_n of 1.15.

5
5N
BB
✓
10
15
20
30
40
50
60
70
80
90
100
110
120
130
140
150
160
170
180
190
200
210
220
230
240
250
260
270
280
290
300
310
320
330
340
350
360
370
380
390
400
410
420
430
440
450
460
470
480
490
500
510
520
530
540
550
560
570
580
590
600
610
620
630
640
650
660
670
680
690
700
710
720
730
740
750
760
770
780
790
800
810
820
830
840
850
860
870
880
890
900
910
920
930
940
950
960
970
980
990
1000
1010
1020
1030
1040
1050
1060
1070
1080
1090
1100
1110
1120
1130
1140
1150
1160
1170
1180
1190
1200
1210
1220
1230
1240
1250
1260
1270
1280
1290
1300
1310
1320
1330
1340
1350
1360
1370
1380
1390
1400
1410
1420
1430
1440
1450
1460
1470
1480
1490
1500
1510
1520
1530
1540
1550
1560
1570
1580
1590
1600
1610
1620
1630
1640
1650
1660
1670
1680
1690
1700
1710
1720
1730
1740
1750
1760
1770
1780
1790
1800
1810
1820
1830
1840
1850
1860
1870
1880
1890
1900
1910
1920
1930
1940
1950
1960
1970
1980
1990
2000
2010
2020
2030
2040
2050
2060
2070
2080
2090
2100
2110
2120
2130
2140
2150
2160
2170
2180
2190
2200
2210
2220
2230
2240
2250
2260
2270
2280
2290
2300
2310
2320
2330
2340
2350
2360
2370
2380
2390
2400
2410
2420
2430
2440
2450
2460
2470
2480
2490
2500
2510
2520
2530
2540
2550
2560
2570
2580
2590
2600
2610
2620
2630
2640
2650
2660
2670
2680
2690
2700
2710
2720
2730
2740
2750
2760
2770
2780
2790
2800
2810
2820
2830
2840
2850
2860
2870
2880
2890
2900
2910
2920
2930
2940
2950
2960
2970
2980
2990
3000
3010
3020
3030
3040
3050
3060
3070
3080
3090
3100
3110
3120
3130
3140
3150
3160
3170
3180
3190
3200
3210
3220
3230
3240
3250
3260
3270
3280
3290
3300
3310
3320
3330
3340
3350
3360
3370
3380
3390
3400
3410
3420
3430
3440
3450
3460
3470
3480
3490
3500
3510
3520
3530
3540
3550
3560
3570
3580
3590
3600
3610
3620
3630
3640
3650
3660
3670
3680
3690
3700
3710
3720
3730
3740
3750
3760
3770
3780
3790
3800
3810
3820
3830
3840
3850
3860
3870
3880
3890
3900
3910
3920
3930
3940
3950
3960
3970
3980
3990
4000
4010
4020
4030
4040
4050
4060
4070
4080
4090
4100
4110
4120
4130
4140
4150
4160
4170
4180
4190
4200
4210
4220
4230
4240
4250
4260
4270
4280
4290
4300
4310
4320
4330
4340
4350
4360
4370
4380
4390
4400
4410
4420
4430
4440
4450
4460
4470
4480
4490
4500
4510
4520
4530
4540
4550
4560
4570
4580
4590
4600
4610
4620
4630
4640
4650
4660
4670
4680
4690
4700
4710
4720
4730
4740
4750
4760
4770
4780
4790
4800
4810
4820
4830
4840
4850
4860
4870
4880
4890
4900
4910
4920
4930
4940
4950
4960
4970
4980
4990
5000
5010
5020
5030
5040
5050
5060
5070
5080
5090
5100
5110
5120
5130
5140
5150
5160
5170
5180
5190
5200
5210
5220
5230
5240
5250
5260
5270
5280
5290
5300
5310
5320
5330
5340
5350
5360
5370
5380
5390
5400
5410
5420
5430
5440
5450
5460
5470
5480
5490
5500
5510
5520
5530
5540
5550
5560
5570
5580
5590
5600
5610
5620
5630
5640
5650
5660
5670
5680
5690
5700
5710
5720
5730
5740
5750
5760
5770
5780
5790
5800
5810
5820
5830
5840
5850
5860
5870
5880
5890
5900
5910
5920
5930
5940
5950
5960
5970
5980
5990
6000
6010
6020
6030
6040
6050
6060
6070
6080
6090
6100
6110
6120
6130
6140
6150
6160
6170
6180
6190
6200
6210
6220
6230
6240
6250
6260
6270
6280
6290
6300
6310
6320
6330
6340
6350
6360
6370
6380
6390
6400
6410
6420
6430
6440
6450
6460
6470
6480
6490
6500
6510
6520
6530
6540
6550
6560
6570
6580
6590
6600
6610
6620
6630
6640
6650
6660
6670
6680
6690
6700
6710
6720
6730
6740
6750
6760
6770
6780
6790
6800
6810
6820
6830
6840
6850
6860
6870
6880
6890
6900
6910
6920
6930
6940
6950
6960
6970
6980
6990
7000
7010
7020
7030
7040
7050
7060
7070
7080
7090
7100
7110
7120
7130
7140
7150
7160
7170
7180
7190
7200
7210
7220
7230
7240
7250
7260
7270
7280
7290
7300
7310
7320
7330
7340
7350
7360
7370
7380
7390
7400
7410
7420
7430
7440
7450
7460
7470
7480
7490
7500
7510
7520
7530
7540
7550
7560
7570
7580
7590
7600
7610
7620
7630
7640
7650
7660
7670
7680
7690
7700
7710
7720
7730
7740
7750
7760
7770
7780
7790
7800
7810
7820
7830
7840
7850
7860
7870
7880
7890
7900
7910
7920
7930
7940
7950
7960
7970
7980
7990
8000
8010
8020
8030
8040
8050
8060
8070
8080
8090
8100
8110
8120
8130
8140
8150
8160
8170
8180
8190
8200
8210
8220
8230
8240
8250
8260
8270
8280
8290
8300
8310
8320
8330
8340
8350
8360
8370
8380
8390
8400
8410
8420
8430
8440
8450
8460
8470
8480
8490
8500
8510
8520
8530
8540
8550
8560
8570
8580
8590
8600
8610
8620
8630
8640
8650
8660
8670
8680
8690
8700
8710
8720
8730
8740
8750
8760
8770
8780
8790
8800
8810
8820
8830
8840
8850
8860
8870
8880
8890
8900
8910
8920
8930
8940
8950
8960
8970
8980
8990
9000
9010
9020
9030
9040
9050
9060
9070
9080
9090
9100
9110
9120
9130
9140
9150
9160
9170
9180
9190
9200
9210
9220
9230
9240
9250
9260
9270
9280
9290
9300
9310
9320
9330
9340
9350
9360
9370
9380
9390
9400
9410
9420
9430
9440
9450
9460
9470
9480
9490
9500
9510
9520
9530
9540
9550
9560
9570
9580
9590
9600
9610
9620
9630
9640
9650
9660
9670
9680
9690
9700
9710
9720
9730
9740
9750
9760
9770
9780
9790
9800
9810
9820
9830
9840
9850
9860
9870
9880
9890
9900
9910
9920
9930
9940
9950
9960
9970
9980
9990
10000

Example 12:

Poly(methyl methacrylate), PMMA, was prepared according to the procedure of Example 3, except that 0.5 g of MMA were used, 0.5 ml of ethyl acetate was employed as a solvent, 2-ethyl bromoisobutyrate (2.5×10^{-5} mol) was used in place of 1-PECl, Cu(I)Br (1.5×10^{-5} mol) was used in place of Cu(I)Cl, and Bpy was present in a molar amount of 4.5×10^{-5} mol. The polymerization was conducted at 100°C for 1.5 h. The polymer was obtained in 95% yield. The $M_{n,SEC}$ of 20,500 was in excellent agreement with the $M_{n,th.}$ of 19,000. The obtained polymer had an M_w/M_n of 1.40.

Example 13:

Polyisoprene was prepared according to the procedure of Example 3, except that 0.45 g of isoprene was used in place of St, 3.77×10^{-5} mol of 1-PECl was used, 3.9×10^{-5} mol of Cu(I)Cl was used, and Bpy was present in a molar amount of 1.2×10^{-4} mol. The polymerization was conducted at 130°C for 45 h. The polymer was obtained in 80% yield. The $M_{n,SEC}$ of 12,700

was in agreement with the $M_{n,th.}$ of 9,500. The obtained polymer had an M_w/M_n of 2.0.

Example 14:

5
10
A PSt-b-PMA block copolymer was produced according to the procedure of Example 3, except that 0.5 g of PSt-Cl ($M_n = 4,000$, $M_w/M_n = 1.45$) was used in place of 1-PECl as the initiator, 1.0 g of MA was used as the monomer, Cu(I)Cl was present in a molar amount of 1.25×10^{-4} mol and Bpy was present in a molar amount of 3.75×10^{-4} mol. The polymerization was conducted at 130°C for 5 h. The polymer was obtained in 95% yield. The $M_{n,SEC}$ of 13,000 was in good agreement with the $M_{n,th.}$ of 11,600. The obtained polymer had an M_w/M_n of 1.35.

Example 15:

15
20
A PSt-b-PMA-b-PSt triblock copolymer was produced as follows. To a flask equipped with a water condenser and a magnetic stirring bar, the initiator α,α' -dibromoxylene (1×10^{-4} mol), CuBr (2×10^{-4} mol), Bpy (6×10^{-4} mol), MA (3 g) and EtOAc (10 ml) were added. Argon was then bubbled through the solution, and the solution was heated at 100°C for 18 h. One ml of solution was withdrawn using a syringe and was analyzed by gas chromatography (GC) and SEC to determine the monomer conversion and M_n , respectively. PMA was obtained in 100%

yield. The $M_{n,SEC}$ of 30,500 was in excellent agreement with the $M_{n,th.}$ of 30,000, and the M_w/M_n of the PMA was 1.3.

Styrene (1 g) was added to the PMA reaction solution, and the mixture was heated at 100°C for 18 h. The triblock polymer was obtained in 100% yield. The $M_{n,SEC}$ of 42,000 was in excellent agreement with the $M_{n,th.}$ of 40,000, and the triblock polymer had an M_w/M_n of 1.45.

Example 16:

A PMA-b-PSt block copolymer was prepared according to the procedure of Example 3, except that 0.5 g of PMA-Cl ($M_n = 2,000$, $M_w/M_n = 1.30$) was used in place of 1-PECl as the initiator, 1.0 g of MA was used as the monomer, Cu(I)Cl was present in a molar amount of 2.5×10^{-4} mol and Bpy was present in a molar amount of 7.5×10^{-4} mol. The polymerization was conducted at 130°C for 10 h. The polymer was obtained in 90% yield. The $M_{n,SEC}$ of 11,500 was in excellent agreement with the $M_{n,th.}$ of 11,000. The obtained polymer had an M_w/M_n of 1.29.

Example 17:

A random P(St-co-MA) copolymer was prepared according to the procedure of Example 3, except that mixture of MA (0.48 g) and St (0.45 g) was used as comonomers, 1-PECl was used in an amount of 3 μ L (2.26×10^{-5} mol), Cu(I)Cl was used in an amount of 2.22×10^{-5} mol and Bpy was present in a molar amount of 6.5×10^{-5} mol. The polymerization was conducted at 130°C for 5 h.

The polymer was obtained in 95% yield. The $M_{n,SEC}$ of 39,000 was in excellent agreement with the $M_{n,th.}$ of 39,100. The obtained polymer had an M_w/M_n of 1.45.

The composition as determined by 1H NMR contained 48% MA, and 52% St.

Example 18:

A random P(St-co-MMA) copolymer was prepared according to the procedure of Example 17, except that mixture of MMA (0.45 g) and St (0.45 g) was used as comonomers, 1-PEBr (3 μ L, 2.2×10^{-5} mol) was used in place of 1-PECl, Cu(I)Br (2.0×10^{-5} mol) was used in place of Cu(I)Cl and Bpy was present in a molar amount of 4.5×10^{-5} mol. The polymerization was conducted at 100°C for 14 h. The polymer was obtained in 90% yield. The $M_{n,SEC}$ of 38,000 was in excellent agreement with the $M_{n,th.}$ of 36,900. The obtained polymer had an M_w/M_n of 1.55.

Example 19:

A six arm star PMA polymer was prepared according to the procedure of Example 3, except that $C_6(CH_2Br)_6$ (1×10^{-4} mol) was used in place of 1-PECl, MA (1 ml, 0.96 g) was used as the monomer, CuBr (1.8×10^{-4} mol) was used in place of Cu(I)Cl, and Bpy was present in a molar amount of 5.8×10^{-4} mol. The polymerization was conducted at 110°C for 45 h. The polymer was obtained in 100% yield. The $M_{n,SEC}$ of 9,600 was in perfect

agreement with the $M_{n,th.}$ of 9,600. The obtained polymer had an M_w/M_n of 2.0.

Example 20:

5 A six-arm star PSt polymer was prepared according to the procedure of Example 3, except that 1.53×10^{-5} mol of $C_6(CH_2Br)_6$ was used in place of 1-PECl. The polymer was obtained in 90% yield. The $M_{n,SEC}$ of 24,100 was in close agreement with the $M_{n,th.}$ of 26,800. The obtained polymer had an M_w/M_n of 1.25.

10 Example 21:

An end-functional PSt having a COOH end group was prepared according to the procedure of Example 3, except that 2-chloropropionic acid (1.74×10^{-5} mol) was used in place of 1-PECl, and the reaction was conducted for 14 h. The polymer was obtained in 50% yield, and had an $M_{n,SEC} = 39,600$ and an $M_w/M_n = 1.45$.

Example 22:


20 A telechelic PMMA with two Br end groups was prepared at 100°C in ethyl acetate according to the procedure of Example 3, except that 1.00×10^{-4} mol of $C_6H_4(CH_2Br)_2$ was used in place of 1-PECl, 0.5 g of MMA was used, 2.00×10^{-4} mol of CuCl was used, and 5.2×10^{-4} mol of Bpy was present. The polymer was obtained in 100% yield after 8 h. The $M_{n,SEC}$ of 4,800 was in

close agreement with the $M_{n,th.}$ of 5,000. The obtained polymer had an M_w/M_n of 1.35.

Example 23:

HBr abstraction (by known methods) of the Br-functional PMMA produced in Example 22 can lead to a telechelic (co)polymer with olefinic end groups, from which a telechelic (co)polymer with primary alcohol end groups can be formed by sequential hydroboration/oxidation (by known methods). Nitration/reduction (by known methods) gives the corresponding amine-ended telechelic (co)polymer.

A Br-ended telechelic (co)polymer ("Br- P_n -Br") can be converted to other groups in one or two step as follows:



Example 24:

An end-functional and in-chain functional PSt with two Br end groups and two central Br groups was prepared at 100°C according to the procedure of Example 3, except that 0.900×10^{-4} mol of CBr_4 was used in place of 1- PECl , 0.5 g of St was

00000000000000000000000000000000

10

TABLE 8

St ATRP in the Presence of Other Transition Metal Complexes Other Than CuCl / Bpy

Initiator	Mt	L	Temp.	time	conv.	Mn,th	Mn,SEC	Mw/Mn
M	M	M	°C	h				
AIBN	CuCl ₂	Bpy	130	3.5h	0.85	7500	6100	2.7
0.11M	0.076M	0.38						
1-PECl	FeCl ₂	(EtO)3P	130	5.5	0.85	21100	19300	3.1
0.075M	0.075	0.375						
1-PECl	CuCl/CuCl ₂	Bpy	130	21	0.80	95500	72500	1.45
0.0075M	0.0075M/"	0.038M						
AIBN	CuCl ₂	bpy	130	21	0.90	25000	18500	1.8
0.034M	0.06	0.14						
AIBN			130	21	0.6		544000	4.50
0.034								
1-PECl	RuCl ₂ (PPh ₃) ₃		130	13	0.9	18400	18300	2.2
0.044M	0.037M							

TABLE 9

MMA ATRP in the Presence of Other Transition Metal Complexes Other Than CuCl / Bpy

Initiator	Mt	L	Temp.(°C)	time	conv.	Mn,th	Mn,SEC	Mw/Mn
(M)	(M)	(M)		hr				
2-ClEPN	FeCl ₂	PPh ₃	130	5	0.85	8460	63100	2.1
0.047M	0.021M	0.073						
"	FeCl ₂	PPh ₃	130	5	0.80	8000	65100	1.8
	0.042	0.14						
"	FeCl ₂	PPh ₃	130	5	0.85	8500	38600	1.76
	0.047	0.28						
"	FeCl ₂	PPh ₃	130	5	0.90	8700	71700	2.1
	0.084	0.3						